

NEW IMPROVED PLEXIN®
(Formerly Puritan #3434)

OCT 7 - 1958

BACTERIA-PROOF FLOOR POLISH

541-79

A self polishing, waxless floor finish containing polyethylene and other polymeric organic materials. Produces a light colored, tough, slip resistant, water resistant, buffable coating with high gloss. For use on Asphalt, Linoleum, Vinyl, Sealed Wood, Terrazzo, Marble, Cork, Rubber and other Composition Tile Floors.

Fights germs and prevents their regrowth. Produces a self-sanitizing surface which continues to fight germs so long as the polish is on the floor. Residual bacteriostatic action helps to maintain a high level of sanitation in hospitals, institutions, offices and homes.

Active Ingredients: (Patented)	0.05%
3,5,4' Tribromosalicylanilide	
5,4' Dibromosalicylanilide	
Inert Ingredients:*	99.95%
*Includes polymeric organic floor polish components.	

CONTAINER (18 pt.): Keep out of reach of children (12 pt.). Harmful if swallowed.

DIRECTIONS

Clean floor thoroughly and remove all old wax and dirt with Puritan's ROBUST or MULSYN. Rinse floor well with clear water and allow to dry.

Apply PLEXIN in thin, even coats using a strand mop or lamb's wool applicator. Allow to dry for 30 minutes before subjecting to traffic. If a second coat is desired, it may be applied 1 1/2 to 4 hours after the first coat has dried. It is unnecessary to buff the final coat.

For maintenance, sweep daily to restore sheen using broom or dust mop treated with PURI-MIST or FINESSE. Mopping with a mild solution of FLOAT, TRIUMPH or BACTILIN will also clean the floor without removing the polish. Regular buffing with polishing brush after sweeping or mopping will restore original lustre.

For removal, use any Puritan heavy duty floor cleaning soap or MULSYN or ROBUST and hot water. Apply the solution with a mop and allow to stand for 10 to 15 minutes before scrubbing with a brush. Pick up scrubbing solution with a mop or vacuum. Rinse floor well and allow to dry.

Keep container tightly closed, Never pour unused portion back into this container.

CAN BE USED AFTER FREEZING. PLEXIN will withstand several freeze-thaw cycles without damage. If it arrives frozen, let it thaw in a warm room, stir thoroughly, and use. Keep from freezing if possible.

U.S.D.A. Registration No. 541-99

Net Vol. Gals.

Quality Control Number.

Manufactured by
PURITAN CHEMICAL COMPANY
Atlanta - Detroit - Houston - Newark - St. Louis