

TROYSAN ZINC 8

(ZINC NAPHTHENATE)

ACTIVE INGREDIENT

Zinc Napthenate	60.
Zinc metal - 8%	

INERT INGREDIENT

Petroleum distillate	40%
----------------------	-----

SOLD FOR MANUFACTURING USE ONLY

FLAMMABLE LIQUID

KEEP AWAY FROM OPEN FLAME

HARMFUL IF TAKEN INTERNALLY

WEIGHT - 400 LBS NET


MANUFACTURED BY

TROY CHEMICAL COMPANY

338 WILSON AVENUE

NEWARK NEW JERSEY

ONE DOCUMENT AVAILABLE



TROYSAN ZINC 8

(ZINC NAPHTHENATE)

ACTIVE INGREDIENT

Zinc Naphthenate	60%
(Zinc metal - 8%)	

INERT INGREDIENT

Petroleum distillate	40%
----------------------	-----

SOLD FOR MANUFACTURING USE ONLY

FLAMMABLE LIQUID

KEEP AWAY FROM OPEN FLAME

HARMFUL IF TAKEN INTERNALLY

WEIGHT - 400 LBS NET

MANUFACTURED BY


TROY CHEMICAL COMPANY

338 WILSON AVENUE

NEWARK, NEW JERSEY

BEST DOCUMENT AVAILABLE

ACCEPTED



TROY CHEMICAL CORP., • 178 W. 45th Street • New York, N.Y. 10036 • Phone: Mitchell 2-5292

TROYSAN ZINC 8 ZINC NAPHTHENATE

PRODUCT

TROYSAN ZINC 8 is a useful fungicide where pale color is desirable. TROYSAN ZINC 8 is a standardized solution of Zinc Napthenate in mineral spirits and is soluble in a broad range of aliphatic and aromatic solvents. TROYSAN ZINC 8 is approximately 50% as effective as its copper counterpart, TROYSAN COPPER 8. Thus twice the concentration of TROYSAN ZINC 8 is required for equal performance.

SPECIFICATIONS

Metal content minimum	8.0%
Approximate weight per gallon (60°F)	7.70 - 8.05
Specific Gravity (80°F)	0.930- 0.970
Color Maximum	Gardner #7
Solids Minimum	60%
Flash Point Minimum	104°F (Penky-Martens Closed Cup)
Viscosity (60°F)	Gardner A-2

USE

Suggested Use: Tents, Fish Nets, Nursery Fabric, Feed Pots, Rope & Twine, Seed bags, Fence Posts, Nursery Lumber, Greenhouse Benches, Seed Bed Covers, Farm Timber & lumber.

How to Use: Simply dilute TROYSAN ZINC 8 in mineral spirits or Stoddard solvent without heating and mix to fully dissolve.

How Much to Use:

1. Textiles: Dip in a 25% solution of TROYSAN ZINC 8 (25% TROYSAN ZINC 8 + 75% solvent)
2. Fences: Dip in 5% solution of TROYSAN ZINC 8 (5% TROYSAN ZINC 8 + 95% solvent).
3. Wood: 1/2 - 50 lb./cu. ft. ZINC 8 via dip.
Where soak (8 hours or longer) treatment is used, 12.5% - 25% TROYSAN ZINC 8 can be used.

ACCEPTED

OCT 3 1966

UNDER THE TRADEMARK REGISTRED
FOR USE AS A FUNGICIDE AND
TO OUR OWN KNOWLEDGE SUBJECT
TO APPROVED COMMENTS

Note: The above attempts to highlight general use for TROYSAN ZINC 8. We welcome the opportunity to discuss specific problems. Our Microbiological and Chemical Laboratories are available to you on a no-charge consulting basis.

All recommendations and information furnished is for guidance only and is without guarantee.