



Cabot's #0241 BLEACHING OIL

MILDEW RESISTANT - WOOD PRESERVATIVE
For a Natural Driftwood Gray on Exterior Wood Siding and Shingles

ONE U. S. GALLON — 3.785 LITERS

WARNING — KEEP OUT OF THE REACH OF CHILDREN
SEE BACK PANEL FOR FURTHER WARNING STATEMENTS

ACTIVE INGREDIENTS:

Water-gas Creosote Oil	81.5%
Folpet	.5%

INERT INGREDIENTS:

Not over	13.0%
	100.0%

WARNING

Keep away from heat and open flame. Avoid contact with skin. Do not breathe vapor or spray mist. Do not get in eyes or on clothing. Close container after each use. Use with adequate ventilation. Harmful if swallowed or absorbed through the skin. May produce severe burns. Do not induce vomiting. Call physician immediately. Before smoking or eating and after using, clean hands thoroughly. Do not contaminate water by cleaning of equipment or disposal of waste and container. Vapors will cause injury if adequate ventilation is not insured. Do not use this product indoors, or any other confined areas, where the vapors may concentrate and cause injury to plant or animal life. Do not reuse container. Destroy when empty.

EPA Reg. No. 43-2.

Samuel Cabot

Incorporated
MANUFACTURING CHEMISTS SINCE 1877
BOSTON, MASSACHUSETTS 02108

8-13 73
43-2

Cabot's
small am
When fir
months' e
driftwood
weatherin
It is for
finish for

Surface
while app
than one

Apply
Two co
vertical si
On horizo
or corner.
DIPPIN
immersed
off excess

TO AC
is recom
important
Bleaching
UNIFO
mixture o
weatherin
PAINT O
Cabot's
exposure.

DRYING
For shi
boards ar
COVERIN
On shir
boards ar
and one b

WARNING

Keep away from fire and flame. Avoid contact with skin. Do not breathe vapor or spray. Avoid contact with eyes or on clothing. Do not use. Use with adequate ventilation. If swallowed or absorbed, do not induce vomiting. Call a physician. Wash thoroughly. Do not contaminate food, clothing, equipment or disposal container. Vapors will cause injury if adequate ventilation is not insured. Do not use this product indoors, or any other confined areas, where the vapors may concentrate and cause injury to plant or animal life. Do not reuse container. Destroy when empty.

EPA Reg. No. 43-2.

Samuel Cabot

Incorporated

MANUFACTURING CHEMISTS SINCE 1877
BOSTON, MASSACHUSETTS 02108

Cabot's #0241 Bleaching Oil is a refined and clarified Creosote Oil containing a small amount of gray pigment and an ingredient that actually bleaches the wood. When first applied, the #0241 gives a delicate gray tone, and during the first few months' exposure it gradually changes the color of new wood to a beautiful, natural driftwood gray. This weathered effect, if derived by nature, requires many years of weathering; whereas Cabot's #0241 Bleaching Oil achieves it in about 6 months.

It is for use on exterior surfaces that have not been previously treated. It is an ideal finish for any type of lumber where a beautiful natural driftwood gray effect is desired.

DIRECTIONS

Surface must be clean and dry. Stir thoroughly before applying and stir occasionally while applying, to maintain a uniform solution. Do not thin. If the job requires more than one can, mix all together in one container and stir till color is uniform.

Apply with a broad flat brush, spray machine or dip shingles before laying.

Two coats are recommended for best appearance and durability. When staining vertical siding begin at the top with several boards and go all the way to the bottom. On horizontal siding begin at one edge and follow thru to a break at a door, window or corner. Do not stain when temperature is below 40°.

DIPPING—dip the shingles in and out rapidly; allow two-thirds of the shingles to be immersed; then throw them in a loose pile and allow them to dry. When dry, brush off excess stain.

TO ACCELERATE WEATHERING ACTION—In order to get uniform weathering, it is recommended that a light spray of water be used to wet the surface. This is most important with wide overhangs and shaded areas. Water activates Cabot's #0241 Bleaching Oil. Note: Allow 2 weeks drying time after staining before wetting surface.

UNIFORM WEATHERING FOR OVERHANGS AND SHADED AREAS—A 50-50 mixture of Cabot's #0241 Bleaching Oil and #0244 Silver Gray will achieve uniform weathering in shaded areas.

PAINT OVER #0241 BLEACHING OIL:

Cabot's #0241 Bleaching Oil can be painted or stained over after two years' exposure.

DRYING TIME:

For shingles and rough wood surfaces, allow 24 hours between coats. For clapboards and smooth siding, allow 3-5 days between coats if possible.

COVERING CAPACITY:

On shingles or rough wood, about 100 square feet per gallon, two coats. On clapboards and smooth wood, 200 to 250 square feet per gallon, two coats. Hand dipping and one brush coat, 2½ to 3½ gallons of stain per square of 16" or 18" shingles.

Clean Your Brushes with Cabot's Brush Cleaner

SELLER MAKES NO WARRANTY, EXPRESSED OR IMPLIED, CONCERNING THE USE OF THIS PRODUCT OTHER THAN INDICATED ON THE LABEL. BUYER ASSUMES ALL RISK OF USE AND/OR HANDLING OF THIS MATERIAL WHEN SUCH USE AND/OR HANDLING IS CONTRARY TO LABEL INSTRUCTIONS.

LITHO IN U.S.A. D.M. CORP.