

ACCEPTED
7-27-71
UNDER
FUNGICID
FOR ECOS
ED UNDEI



M & S CREOSOTE OIL

FOR USE ON ROPE: For prevention of fungal rot and decay, dip rope into MARTIN'S M&S CREOSOTE and soak until all fibers are saturated (minimum of 10 minutes for 1/2 inch rope).

TREE WOUND DRESSING: For prevention of fungus and bacterial decay, apply as a paint to all pruning cut surfaces.

CAUTION: Harmful if swallowed. Avoid breathing vapor, fumes or spray mist. Avoid contact with skin. Use with adequate ventilation. Do not use or store near heat or open flame. Do not reuse empty containers. Destroy by perforating or crushing and burying in safe place. DO NOT CONTAMINATE WATER BY CLEANING OF EQUIPMENT OR DISPOSAL OF WASTES. DO NOT CONTAMINATE FOOD OR FEEDSTUFFS.

U.S.D.A. Registration Number 299-156

Preservative and tree wound dressing for the prevention of fungal rot and decay on:

WOOD ROPE CANVAS

Meets American Wood Preservers Association Standard
PI-65 For Coal Tar Creosote

CONTENTS: 1 GALLON

CAUTION: Keep Out of Reach of Children
SEE BACK PANEL FOR OTHER CAUTIONS

ACTIVE INGREDIENTS:
Creosote Oil 97.00%
INERT INGREDIENTS: 3.00%

DIRECTIONS

FOR USE ON WOOD: For prevention of fungal rot and decay on foundations, fence posts, farm gates, board fences, bridge timbers, factory buildings, shingle roofs, and exposed woodwork, use one or two liberal brush or spray coats of MARTIN'S M&S CREOSOTE. Wood to be treated should be dry and well seasoned and free of bark. For fence posts or other wood members to be placed in contact with the soil, use 2 or more liberal brush or spray coats or soak the area from 2 to 6 inches above ground line to the bottom of post for 12 to 48 hours. Do not use inside barns, animal sleeping quarters, milk room, hog pens, sheep folds or silos.

FOR USE ON CANVAS TARPULINS: For prevention of fungal rot and bacterial decay, apply MARTIN'S M&S CREOSOTE by brushing or spraying. Saturate all fibers completely.

606 W. Main St. *C. J. Martin Company* Nacogdoches, Texas 75961

AC
7-27-71
DRETT
PUN
ECL
E. HINE



M & S CREOSOTE OIL

FOR USE ON ROPE: For prevention of fungal rot and decay, dip rope into MARTINS M&S CREOSOTE and soak until all fibers are saturated (minimum of 10 minutes for 1/2 inch rope).

TREE WOUND DRESSING: For prevention of fungus and bacterial decay, apply as a paint to all pruning cut surfaces.

CAUTION: Harmful if swallowed. Avoid breathing vapor, fumes or spray mist. Avoid contact with skin. Use with adequate ventilation. Do not use or store near heat or open flame. Do not reuse empty containers. Destroy by perforating or crushing and burying in safe place. **DO NOT CONTAMINATE WATER BY CLEANING OF EQUIPMENT OR DISPOSAL OF WASTES. DO NOT CONTAMINATE FOOD OR FEEDSTUFFS.**

U.S.D.A. Registration Number 299-156

Preservative and tree wound dressing for the prevention of fungal rot and decay on:
WOOD ROPE CANVAS
Meets American Wood Preservers Association Standard
PI-65 For Coal Tar Creosote

CONTENTS: 1 GALLON

CAUTION: Keep Out of Reach of Children
SEE BACK PANEL FOR OTHER CAUTIONS

ACTIVE INGREDIENTS:
Creosote Oil 97.00%
INERT INGREDIENTS: 3.00%

DIRECTIONS

FOR USE ON WOOD: For prevention of fungal rot and decay on foundations, fence posts, farm gates, board fences, bridge timbers, factory buildings, shingle roofs, and exposed woodwork, use one or two liberal brush or spray coats of MARTINS M&S CREOSOTE. Wood to be treated should be dry and well seasoned and free of bark. For fence posts or other wood members to be placed in contact with the soil, use 2 or more liberal brush or spray coats or soak the area from 2 to 6 inches above ground line to the bottom of post for 12 to 48 hours. Do not use inside barns, animal sleeping quarters, milk room, hog pens, sheep folds or silos.

FOR USE ON CANVAS TARPULINS: For prevention of fungal rot and bacterial decay, apply MARTINS M&S CREOSOTE by brushing or spraying. Saturate all fibers completely.

606 W. Main St. *C. J. Martin Company* Nacogdoches, Texas 75961