



INDUSTRIAL MAINTENANCE

**MARINE FINISHES
BOTTOM PAINT
ANTIFOULING
TROPICAL RED**

360-756

FOR PROFESSIONAL USE
NOT FOR RETAIL SALE

SPECIFICATIONS

DRYING TIME - - - 1 hour at 70°F.
THEORETICAL COVERAGE - - 363
 to 484 sq. ft. per gallon at 1.5 to 2.0 mils
 dry film thickness.
THINNER - - Brush or Roller, Du Pont
 T-8894. Spray, T-3033, up to 1/2 pint
 per gallon.
NUMBER OF COATS
 1 coat over Du Pont Bare Plate Primer
 and Anticorrosive Primer.

ACTIVE INGREDIENT Cuprous Oxide
 (Total copper as metallic 14.6%)
INERT INGREDIENTS

Recommended for below-the-water-line protection from
 barnacles and marine fouling animals in tropical waters.

DIRECTIONS

Surface Preparation: Surfaces must be clean and dry.
Application: Stir thoroughly. Apply with a good quality
 brush or roller. Can also be sprayed but local health
 regulations must be followed.
Note: Immerse within 16 to 24 hours after application.

21 9XX 055-1266

16.5%
83.5%

CAUTION! COMBUSTIBLE

Keep away from heat and open flame. Avoid prolonged contact with skin and breathing
 of vapor or spray mist. Close container after each use
 Use with adequate ventilation.

KEEP OUT OF THE REACH OF CHILDREN

Contains lead compounds. Harmful if swallowed. Do not apply on toys, furniture or
 interior surfaces which might be chewed by children.

FIVE U.S. GALLONS 18.925 Liters
 USDA REG. NO. 352-318

E. I. DU PONT DE NEMOURS & CO. (INC.), Wilmington, Delaware

RECEIVED
 April 7, 1967
 21-9-055-0564
 UNDER THE FEDERAL INSECTICIDE
 FUNGICIDE AND RODENTICIDE ACT
 FOR ECONOMIC POISON REGISTERED
 UNDER NO. 352-318
 TO ATTACHED COMMENTS.

352-318