

DIRECTIONS: GRO-NOT is easy to use and gives rapid results. Hold nozzle down, 8 to 10 inches from vegetation to be sprayed, for complete contact kill. Do not water immediately after spraying. Fast, easy application. Repeat application if necessary.

GRO-NOT is non-selective. Spray only that foliage you wish to kill. Do not use in flower or vegetable beds, or on lawns. Do not use during periods of high winds to avoid spray drift. GRO-NOT can be used around shrubbery beds if extreme caution is exercised to prevent drift on any desirable foliage.

SHAKE WELL BEFORE USING.

# PETTIT

marine  paint

ACTIVE INGREDIENT	
Pb's (tributyltin) Oxide	4.6%
INERT INGREDIENTS	
	95.4%
	100.0%
EPA Reg. No. 390-30	

# UNEPOXY

**ANTI FOULING**

T 32 FL.OZ.(1 QT.)

**CAUTION** KEEP OUT OF THE REACH OF CHILDREN. OTHER PRECAUTIONS ON BACK PANEL.

**PETTIT PAINT CO., INC.**

**BOROUGH OF ROCKAWAY  
NEW JERSEY 07866**

**SAN LEANDRO  
CALIFORNIA 94577**

### UNEPOXY WHITE

Unepoxy is an effective hard racing antifouling boat bottom paint for various waters. It can be applied over PETTIT'S VINYLCLIDE RED and most aged non-antifouling hard racing finishes. A small test area of Unepoxy on aged hard racing finishes is recommended to determine adhesion and compatibility to the old finish. Old, soft, or semi-hard antifouling paints should be removed for best adhesion. Allow a minimum of 2 hours cure time between coats. After the final coat is applied, the boat may be launched after 4 hours minimum to within 2 months maximum.

**FIBERGLASS:** Wash fiberglass with PETTIT'S #120 BRUSHING THINNER to remove parting agent, grease, and dirt. Sand thoroughly with medium grit sandpaper to dull the glossy fiberglass surface. No undercoat is required before using Unepoxy on fiberglass. Apply 2 coats of Unepoxy.

**WOODEN HULLS:** Old antifouling paint should be scraped to bare wood. PETTIT'S VINYLCLIDE RED or aged non-antifouling hard racing finishes should be sanded thoroughly. If priming is necessary, apply one coat of PETTIT'S RED LEAD PRIMER and let dry 24 hours. Then apply 2 coats of Unepoxy.

**STEEL HULLS:** Remove all rust and scale from metal surface by scraping and wire brushing. Wash the surface with PETTIT'S #120 BRUSHING THINNER to remove grease and imbedded dirt. Apply one coat of PETTIT'S VINYL METAL PRIMER to bare metal and let dry 4 hours. Follow with 2 coats of PETTIT'S VINYL RED UNDER-COATER and let dry 2 hours between coats and 4 hours before applying 2 coats of Unepoxy.

**CLEANING AND THINNING:** Use PETTIT'S #120 BRUSHING THINNER.

### CAUTION

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION. CONTAINS TIN COMPOUNDS AND AROMATIC HYDROCARBONS. INDUCE VOMITING. Drink milk. Avoid breathing spray mist. Do not get in eyes, on skin, or on clothing. In case of skin contact, remove contaminated clothing and immediately wash skin with soap and water. Flush eyes with water. Get medical attention if irritation persists. Avoid storage near food or feed products. Do not apply to any surface that will be used by children. May be absorbed through skin. Wash contaminated clothes before re-use. Do not reuse container. Destroy when empty. Do not use, pour, spill, or store near heat or open flame. Use with adequate ventilation.

ONE QUART U.S. STANDARD

KEEP OUT OF REACH OF CHILDREN.