

FEDERAL INSECTICIDE
AND RODENTICIDE ACT
MICROBICIDE P. G. SIER-
NO. 390-6 SUBJECT
SCHEDULED COMMERCE'S

390-6

PETTIT
marine  *paint*

ANTI-FOULING

1635

RED

TROPICOP

U.S. QUART LIQ.

PETTIT PAINT CO., INC.

SAN LEANDRO, CALIF. BELLEVILLE, N. J.

PETTIT TROPICOP ANTI-FOULING PAINT

This is a plastic type of strong anti-fouling paint, which incorporates the latest research developments in the marine field.
TROPICOP RED may be used on either steel or wooden boats. It provides protection against barnacles, teredo worms, and other marine growths.
DO NOT USE ON ALUMINUM BOATS.

DIRECTIONS

The bottom to be painted should be dry and the old paint thoroughly cleaned. Old paint in poor condition should be removed.
Stir the paint thoroughly at first and then occasionally during application.
Allow at least six hours drying time between coats and after the final coat before launching.

WOODEN HULLS — Prime all bare wood with PETTIT'S RED LEAD PRIMER and dry overnight, sand lightly. Apply two coats of TROPICOP RED. On repaint work, apply two coats of TROPICOP.

STEEL HULLS — Remove all rust, grease, and scale from metal surface. Apply one coat of PETTIT'S VINYL METAL PRIMER to bare metal. Follow with two coats of PETTIT ZINC CHROMATE PRIMER or PETTIT VINYL RED UNDERCOATER. Finally, apply two coats of TROPICOP RED. On repaint work, apply two coats.

Use PETTIT'S #120 BRUSHING THINNER for thinning, if necessary, and for cleaning brushes.

USDA Reg. No. 390-6

DANGER  **POISON**

HARMFUL OR FATAL IF SWALLOWED COMBUSTIBLE.

CONTAINS COPPER AND PETROLEUM DISTILLATE. DO NOT INDUCE VOMITING. Do not apply on window sills, toys, furniture, or interior surfaces which may be used by children. Avoid prolonged contact with skin and breathing vapor or spray mist. Wash thoroughly after handling and before eating or smoking. Keep away from heat and open flame. Close container after each use.

Use with adequate ventilation.

KEEP OUT OF THE REACH OF CHILDREN.

ONE QUART U.S. STANDARD

IMPERIAL MEASURE 33 FL. OZ.