

PETTIT
marine  *paint*

ANTI-FOULING

1340

GREEN

YACHT COPPER

This product contains:
petroleum distillates:

KEEP OUT OF REACH OF CHILDREN.

32 FL.OZ. (1 QT.) 946 ml

WARNING! SEE SIDE PANEL FOR
ADDITIONAL PRECAUTIONARY STATEMENTS.

ACTIVE INGREDIENTS
Zinc Oxide 14.00%
ST. IRON OXIDE 84.00%
COPPER AS METALLIC 12.4%

PETTIT PAINT CO., INC.

BOROUGH OF ROCK

PETTIT

marine  paint

ANTI-FOULING

1340

GREEN

YACHT COPPER

ACTIVE INGREDIENTS
Copper Oxide 1.00%
BEST INCREASING 1.00%
1.00%

COPPER AS METALLIC 12.4%

This product contains petroleum distillates

KEEP OUT OF REACH OF CHILDREN.

WARNING! SEE SIDE PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS.

PETTIT PAINT CO., INC.

BOROUGH OF ROCKAWAY, N.J. 07866 - SPRING VALLEY, CALIF. 92077

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS
WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe sanding dust, vapor or spray mist. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

If swallowed: Drink promptly a large quantity of milk, egg whites, gelatin solution or, if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention

If in eyes: Flush with plenty of water. Get medical attention.

If on skin: Wash with plenty of soap and water. Get medical attention.

If inhaled: Remove victim to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Get medical attention.

ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARD

COMBUSTIBLE! Do not use or store near heat or open flame.

(continued on right hand panel)

340-12

(continued from left hand panel)

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

NOTE - When product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

Yacht Copper Paint is an anti-fouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE & DISPOSAL

Pesticide, spray mixture, or rinsate that cannot be used according to label instructions must be disposed of according to Federal or approved state procedures under Subtitle C of the Resource Conservation and Recovery Act.

Container Disposal

Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other approved state and local procedures.

E.P.A. REG. NO..... 390-12
E.P.A. EST. NO..... 390-NJ-1

PRODUCT DESCRIPTION: Yacht Copper Paint is a soft protective paint for use on wood boat bottoms. It can be applied over most aged antifouling coatings. Old peeling antifouling paints should be removed for best adhesion. Yacht Copper Paint can be scrubbed easily when hauled out so there will not be much film build-up from year to year. The antifouling mechanism works both by erosion and leaching.

PREPARATION OF SURFACE: The surface to be painted should be dry, clean, and oil free. It should be properly prepared by solvent cleaning and/or sanding before any primers or paints are applied. Follow the recommended systems below. When sanding old antifouling paint, use a face mask to prevent the inhalation of sanding dust.

APPLICATION AND TEMPERATURE: Yacht Copper Paint can be applied by brush, roller or spary. The work should be done between 9:00 a.m. and 4:00 p.m. under good drying conditions. The temperature range of application is 40° to 90° F. Two coats should be applied for best antifouling protection.

PREPARATION OF PAINT: Yacht Copper Paint contains cuprous oxide. As a result, there is a tendency for settling to occur especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible shake the can of paint on a mechanical paint shaker. Before using check the sides and bottom of the can to make sure all the pigment has been mixed in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment; then remix the two parts together thoroughly.

THINNER: Use Pettit's 12120 Brushing Thinner for thinning the Yacht Copper Paint on a warm windy day or for cleaning up equipment. Do not over thin Yacht Copper Paint or inadequate paint application will occur. Use Pettit 12121 Spraying Thinner for spray application.

DRY TIMES: Let the first coat of Yacht Copper Paint dry overnight before applying the second coat. After the second coat is applied, let the paint dry at least six hours before immersing the boat. Maximum immersion time is 48 hours.

COVERAGE: Unepoxy covers approximately 500 square feet per gallon.

MAINTENANCE OF ANTIFOULING PAINT: No antifouling paint can be effective under all conditions of exposure. Manmade pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water, and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the boat be checked several times a month to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

PAINT SYSTEMS

WOODEN HULLS: Old antifouling paint should be thoroughly sanded or scraped to bare wood. If priming is necessary on bare wood, apply one coat of Pettit's Red Lead Primer and let dry for 24 hours. Sand lightly and apply two coats of Yacht Copper Paint.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS AND OUTDRIVES.