

UNDER THE FEDERAL INSECTICIDE ACT
EPA REG. NO. 100-100000000
EPA EST. NO. 100-100000000
EPA REG. NO. 100-100000000
EPA EST. NO. 100-100000000

PETTIT

marine  paint

UNEPOXY

CAUTION
KEEP OUT OF THE
REACH OF CHILDREN.
OTHER WARNINGS
ON BACK PANEL

1922
ANTI-FOULING
ATLANTIC
BRONZE

ONE U.S. PINT LIQ.

- 40.6% Aromatic Hydrocarbons
 - 36.5 Copper Powder
 - 7.5 Epoxy Acrylic Ester
 - 5.4 Magnesium Silicate
 - 5.0 Resin
 - 3.5 Bis (Tri-n-butyltin) Oxide
 - 100.0%
-
- Active Ingredients
 - 36.0% Copper Powder
 - 3.5 Bis (Tri-n-butyltin) Oxide
 - 60.5 Inert Ingredients
 - 100.0%

USDA #390-13

UNEPOXY BRONZE

Unepoxy Bronze is an effective hard racing anti-fouling boat bottom paint designed for various waters. It can be applied over PETTIT'S VINYLICIDE RED and most non-anti-fouling hard racing finishes. A small test area of Unepoxy on aged hard racing finishes is recommended to determine adhesion and compatibility to the old finish. Old, soft or semi-hard anti-fouling paints should be removed for best adhesion. Allow a minimum of 2 hours cure time between coats. After the final coat is applied, the boat may be launched after 4 hours minimum to within 2 weeks maximum.

FIBERGLASS: Wash fiberglass with PETTIT'S #120 BRUSHING THINNER to remove parting agent grease and dirt. Sand thoroughly with medium grit sandpaper to dull the glossy fiberglass surface. No undercoat is required before using Unepoxy on fiberglass. Apply 2 coats of Unepoxy.

WOODEN HULLS: Old anti-fouling paint should be scraped to bare wood. PETTIT'S VINYLICIDE RED or aged non-anti-fouling hard racing finishes should be sanded thoroughly. If priming is necessary, apply one coat of PETTIT'S RED LEAD PRIMER and let dry 24 hours. Then apply 2 coats of Unepoxy.

CLEANING AND THINNING: USE PETTIT'S #120 BRUSHING THINNER.
DO NOT USE THIS PRODUCT ON STEEL AND ALUMINUM HULLS.

POISON DANGER

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION

CONTAINS COPPER AND TIN COMPOUNDS AND AROMATIC HYDROCARBONS. INDUCE VOMITING.

Drink milk. Avoid breathing spray mist. Do not get in eyes, on skin, or on clothing. In case of skin contact, remove contaminated clothing and immediately wash skin with soap and water. Flush eyes with water. Get medical attention if irritation persists. Avoid storage near food or feed products. Do not apply to any surface that will be used by children. May be absorbed through skin. Wash contaminated clothes before re-use. Use with adequate ventilation. KEEP OUT OF REACH OF CHILDREN.

ONE PINT U.S. STANDARD

PETTIT PAINT CO., INC.

SAN LEANDRO, CALIF. BELLEVILLE, N. J.

UNDER THE FEDERAL INSECTICIDE
 FUNGICIDE AND RODENTICIDE ACT
 FOR ECONOMIC POISON REGISTERED
 UNDER NO. 390-13 SUBJECT
 TO ATTACHED COMMENTS.

390-13

PETTIT
marine paint

UNEPOXY BRONZE
 1925

**ANTI-FOULING
 ATLANTIC
 BRONZE**

ONE U.S. PINT LIQ.

PETTIT PAINT CO., INC.

40.6%	Aromatic Hydrocarbons
34.0	Copper Powder
9.5	Epoxy Acrylic Ester
5.4	Magnesium Silicate
5.0	Resin
3.5	Bis (Tri-n-butyltin) Oxide
100.0%	Active Ingredients
36.0%	Copper Powder
3.5	Bis (Tri-n-butyltin) Oxide
60.5	Inert Ingredients
100.0%	
	USDA #390-13

UNEPOXY BRONZE

Unepoxy Bronze is an oil-free lead racing anti-fouling boat bottom paint designed for various waters. It can be applied over PETTIT'S VINYLCIDE RED and most previously applied hard racing finishes. A small quantity of the new oil-free hard racing finish is recommended to determine adhesion and compatibility for the old finish. Old, soft or weathered anti-fouling paints should be removed for best adhesion. Allow a minimum of 2 hours cure time between coats. After the final coat is applied, the boat will be finished after 4 hours minimum to within 2 weeks maximum.

FIBERGLASS: Wash fiberglass with PETTIT'S #120 BRUSHING THINNER to remove particles, grease and dirt. Good thoroughly with thinner and scrubbing to get the glossy appearance restored. No undercoat is applied over the Unepoxy.

WOODEN HULLS: Old anti-fouling paint should be scraped to bare wood. PETTIT'S VINYLCIDE RED or good non-anti-fouling hard racing finishes should be applied, depending on priming is necessary, apply one coat of PETTIT'S RED LEAD PRIMER and let dry 24 hours. Then apply 2 coats of Unepoxy.

CLEANING AND THINNING: USE PETTIT'S #120 BRUSHING THINNER.
 DO NOT USE THIS PRODUCT ON STEEL AND ALUMINUM HULLS.

POISON DANGER

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION

CONTAINS COPPER AND TIN COMPOUNDS AND AROMATIC HYDROCARBONS. INDUCE VOMITING.

Do not get on face, neck, or hands. Do not get in eyes. If in eyes, flush with water. If on face, wash with water. If on hands, wash with soap and water. If on clothing, wash with soap and water. If on skin, wash with soap and water. If on eyes, flush with water. If on face, wash with water. If on hands, wash with soap and water. If on clothing, wash with soap and water.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

ONE PINT U.S. STANDARD

SAN LEANDRO, CALIF. BELLEVILLE, N. J.