

PETTIT



UNEPOXY

ANTI FOULING

1924

PACIFIC BRONZE

Active
Ingredients
35.93% Copper

4.13%



UNEPOXY BRONZE

Unepoxy is an effective hard racing antifouling boat bottom paint for various waters. It can be applied over PETTIT'S VINYLICIDE RED and most aged non-antifouling hard racing finishes. A small test area of Unepoxy on aged hard racing finishes is recommended to determine adhesion and compatibility to the old finish. Old, soft, or semi-hard antifouling paints should be removed for best adhesion. Allow a minimum of 2 hours curing time between coats. After the final coat is applied, the boat may be launched after 8 hours minimum to within 2 months maximum.

FIBERGLASS: Wash fiberglass with PETTIT'S #12120 BRUSHING THINNER to remove parting agent, grease, and dirt. Sand thoroughly with medium grit sandpaper to dull the glossy fiberglass surface. Apply 2 coats of Unepoxy. An alternate system for fiberglass is to wash with PETTIT'S #15095 MUST DEWAXER and then apply a coat of 9399 SANDLESS PREP COAT. Do not sand the Prep Coat. Apply 2 coats of Unepoxy making sure the first coat of Unepoxy is applied to the Prep Coat within 24 hours after the Prep Coat has been applied.

WOODEN HULLS: Old antifouling paint should be scraped to bare wood. PETTIT'S VINYLICIDE RED or aged non-antifouling hard racing finishes should be sanded thoroughly. If priming is necessary on bare wood, apply 1 coat of PETTIT'S RED LEAD PRIMER and let dry 24 hours. Sand lightly and apply 2 coats of Unepoxy.

CLEANING AND THINNING: Use PETTIT'S #12120 BRUSHING THINNER.

DO NOT USE THIS PRODUCT ON STEEL AND ALUMINUM HULLS.
STIR THOROUGHLY BEFORE USING.

CAUTION

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION.

CONTAINS COPPER AND TIN COMPOUNDS AND AROMATIC HYDROCARBONS. INDUCE VOMITING. Drink milk. Do not breathe spray mist. Do not get in eyes, on skin, or on clothing. May be absorbed through skin. In case of skin contact, remove contaminated clothing and immediately wash with soap and water. Flush eyes with water. Get medical attention if irritation persists. Avoid storage near food or feed products. Do not apply to any surface that will be used by children. Do not reuse empty container. Destroy it by perforating or crushing. Do not contaminate water used for irrigation or domestic purposes. Bury or discard in a safe place. Use with adequate ventilation.

KEEP OUT OF REACH OF CHILDREN.

ONE QUART U.S. STANDARD

IMPERIAL MEASURE 33 FL. OZ.

NET 32 FL. OZ. (1 QT.)

CAUTION KEEP OUT OF THE REACH OF CHILDREN.
OTHER WARNINGS ON BACK PANEL

PETTIT PAINT CO., INC.

SAN LEANDRO, CALIF. BELLEVILLE, N. J.

ACCEPTED WITH COMMENTS