

# PETTIT

marine  paint

# UNEPOXY

## ANTI FOULING

1320

TROPIC GREEN

NET 32 FL.OZ. (1 QT.)

**CAUTION** KEEP OUT OF THE REACH OF CHILDREN.  
OTHER WARNINGS ON BACK PANEL

## PETTIT PAINT CO., INC.

- 54.0% Cuprous Oxide
- 23.2 Aromatic Hydrocarbons
- 7.3 Titanium Dioxide
- 6.0 Rosin
- 5.0 Epoxy Acrylic Ester
- 2.5 Phalocyanine Green
- 1.0 Chrome Yellow
- 1.0 Bis (Tributyltin) Oxide

- 100.0% Active Ingredients
- 54.0% Cuprous Oxide
- 1.0 Bis (Tributyltin) Oxide
- 45.0 Inert Ingredients

100.0% **ACCEPTED**

UNDER  
EUNICIDE  
ECONOMIC  
UNDER NO.

390-23

### UNEPOXY COLORS

Unepoxy is an effective hard racing antifouling boat bottom paint for various waters. It can be applied over PETTIT'S VINYL-CIDE RED and most aged non-antifouling hard racing finishes. A small test area of Unepoxy on aged hard racing finishes is recommended to determine adhesion and compatibility to the old finish. Old, soft or semi hard antifouling paints should be removed for best adhesion. Allow a minimum of 2 hours curing time between coats. After the final coat is applied, the boat may be launched after 8 hours minimum to within 2 months maximum.

**FIBERGLASS:** Wash fiberglass with PETTIT'S #12120 BRUSHING THINNER to remove parting agent, grease, and dirt. Sand thoroughly with medium grit sandpaper to dull the glossy fiberglass surface. Apply 2 coats of Unepoxy. An alternate system for fiberglass is to wash with PETTIT'S #15095 MUST DEWAXER and then apply a coat of 9399 SANDLESS PREP COAT. Do not sand the Prep Coat. Apply 2 coats of Unepoxy making sure the first coat of Unepoxy is applied to the Prep Coat within 24 hours after the Prep Coat has been applied.

**WOODEN HULLS:** Old antifouling paint should be scraped to bare wood. PETTIT'S VINYL-CIDE RED or aged non-antifouling hard racing finishes should be sanded thoroughly. If priming is necessary on bare wood, apply 1 coat of PETTIT'S RED LEAD PRIMER and let dry for 24 hours. Sand lightly and apply 2 coats of Unepoxy.

**STEEL HULLS:** To remove old rust and scale from the metal surface, scraping, sandblasting, or wire brushing. Wash the surface with PETTIT'S #12120 BRUSHING THINNER to remove grease and embedded dirt. Apply 1 coat of PETTIT'S VINYL METAL PRIMER to bare metal and let dry 4 hours. Follow with 2 coats of PETTIT'S VINYL RED UNDERCOATER and let dry 2 hours between coats and 4 hours before applying 2 coats of Unepoxy.

**CLEANING AND THINNING:** Use PETTIT'S #12120 BRUSHING THINNER.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS. STIR PAINT THOROUGHLY BEFORE USING.

### CAUTION

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION.

CONTAINS COPPER AND TIN COMPOUNDS AND AROMATIC HYDROCARBONS. INDUCE VOMITING. Drink milk. Do not breathe spray mist. Do not get in eyes, on skin, or on clothing. May be absorbed through skin. In case of skin contact, remove contaminated clothing and immediately wash with soap and water. Wash clothes before reuse. Flush eyes with water. Get medical attention if irritation persists. Avoid storage near food or food products. Do not apply to any surface that will be used by children. Do not reuse empty container. Destroy it by perforation or crushing. Bury or discard in a safe place.

Use with adequate ventilation.

KEEP OUT OF REACH OF CHILDREN.

ONE QUART U.S. STANDARD

IMPERIAL MEASURE 33 FL. OZ.

SAN LEANDRO, CALIF. BELLEVILLE, N. J.

ACCEPTED WITH COMMENTS