

PETTIT

marine  paint

UNEPOXY

ANTI FOULING
1622 RED

ATLANTIC FORMULA

ACTIVE INGREDIENTS

Cuprous Oxide 52.00%

Bis (Tributyltin) Oxide 2.30%

INERT INGREDIENTS 45.70%

COPPER AS METALLIC 46.20%

This product contains petroleum distillates.

32 FL.OZ. (1 QT.) 946 ml

KEEP OUT OF REACH OF CHILDREN.

DANGER! SEE SIDE PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS.

PETTIT PAINT CO., INC.

BOROUGH OF ROCKAWAY, N.J. 07866 - SP

ETTIT
re  *paint*

EPOXY

**ANTI FOULING
1622 RED
ANTIC FORMULA**

ACTIVE INGREDIENTS

Cuprous Oxide 52.00%

Bi (Tributyltin) Oxide 2.30%

INERT INGREDIENTS 45.70%

100.00%

COPPER AS METALLIC 46.20%

This product contains petroleum distillates.

KEEP OUT OF REACH OF CHILDREN.

DANGER! SEE SIDE PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS.

PAINT CO., INC.

BOROUGH OF ROCKAWAY, N.J. 07866 - SPRING VALLEY, CALIF. 92077

SAFETY DATA SHEET
SECTION 2: HAZARD IDENTIFICATION

Irritative. Causes skin irritation. Avoid contact with skin, eyes, nose, mouth, or clothing. Avoid breathing vapors, mists, or dusts. May be fatal if swallowed. Causes eye irritation. This product may be a dermal sensitizer. Avoid contact with skin, eyes, or clothing. Wash thoroughly with soap and water after handling and before eating, drinking, or smoking.

2.1 Hazard Classification

Swallow: Harmful (H302). Causes eye irritation (H312). May be fatal if swallowed (H302). Causes skin irritation (H315). May be a dermal sensitizer (H317). Wash thoroughly with soap and water after handling and before eating, drinking, or smoking.

2.2 Label Elements

Signal Word: Harmful
Hazard Statements: H302, H312, H315, H317
Prevention: P201, P202, P273, P302+P352, P305+P351+P338, P312, P332+P313, P337+P313, P340+P340+P340, P501

2.3 Environmental

Very slightly flammable (H228). May be harmful to aquatic life (H411). Do not release into the environment.

2.4 Stability and Reactivity

Stable under normal conditions. Do not mix with strong oxidizers. Do not mix with strong acids. Do not mix with strong bases. Do not mix with strong solvents. Do not mix with strong reducing agents. Do not mix with strong acids. Do not mix with strong bases. Do not mix with strong solvents. Do not mix with strong reducing agents.

PHYSICAL OR CHEMICAL HAZARD
COMBUSTIBLE! Do not use or store near heat or open flame.

(continued on right hand panel)

11111
22222
33333
44444
55555
66666
77777
88888
99999
00000

11111
22222
33333
44444
55555
66666
77777
88888
99999
00000

(continued from left hand panel)

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

NOTE - When product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

EPOXY is an anti-fouling protective coating resistant to algae, barnacles and other marine fouling.



STORAGE & DISPOSAL

Pesticide, spray mixture, or rinse water that cannot be used according to label instructions must be disposed of according to Federal or approved state procedure under Subtitle C of the Resource Conservation and Recovery Act.

Container Disposal

Empty containers should be cleaned, reconditioned, or repaired and disposed of in accordance with other approved state and local procedures.

E.P.A. REG. NO.390-27
E.P.A. EST. NO.390-NJ-1



PREPARATION OF SURFACE: The surface to be painted should be dry, clean, and free of any loose material. It should be free of any oil, grease, and dirt. The surface should be sanded with 80-120 sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt. Sand thoroughly with 80-120 sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt. The surface should be sanded with 80-120 sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt.

APPLICATION AND TEMPERATURE: Unepoxy can be applied by brush, roller or spray. Work should be done between 3:00 a.m. and 4:00 p.m. under good drying conditions. The temperature during application is 40° to 90° F. Two coats should be applied for best results.

APPLICATION: Unepoxy should be applied with a brush. When using a brush, there is a tendency for settling to occur especially if the paint has been in the can for several months. It is necessary to shake the can of paint on a regular basis to keep the paint from settling. If possible, shake the can of paint on a regular basis to keep the paint from settling. If possible, shake the can of paint on a regular basis to keep the paint from settling. If possible, shake the can of paint on a regular basis to keep the paint from settling.

THINNER: Use Pettit's 12120 Brushing Thinner for thinning the Unepoxy. Do not use thinner that is not over thin. Do not use thinner that is not over thin. Do not use thinner that is not over thin.

DRYING: After applying the Unepoxy, let the boat dry for at least eight hours or preferably overnight before immersing the boat. Under adverse drying conditions let the boat dry overnight to make sure all the solvent is out of the paint film. Maximum immersion time is two months.

COVERAGE: Unepoxy covers approximately 400 square feet per gallon.

MAINTENANCE OF ANTIPOULING PAINT: No antifouling paint can be effective under all conditions of exposure. Manmade pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water, and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the boat be checked several times a month to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

PAINT SYSTEMS **BEST DOCUMENT AVAILABLE**

FIBERGLASS: Wash the fiberglass with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt. Sand thoroughly with 80-120 sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt. Sand thoroughly with 80-120 sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface with Pettit's 12120 Brushing Thinner or 15095 Solvent to remove parting agent, grease, and dirt.

GELCOTE: Remove all antifouling paint by sanding or using Pettit's 15095 Solvent. Sand the gelcote and fill any voids with Pettit's 7190 Polyester Mender. Sand smooth, apply a coat of Pettit's 4027 Polyepoxy Undercoater. Let dry 24 hours. Sand lightly and then apply two coats of Unepoxy.

ALUMINUM HULLS: All metal surfaces should be thoroughly sanded or scraped
to remove old paint and rust. Wash the surface with Pettit's
Red Lead Primer and let dry for 24 hours. Sand lightly and apply two coats
of Unepoxy.

STEEL HULLS, UNDERWATER METAL PARTS, LEAD KEELS: To remove old rust and scale
from the metal surface scrape or sandblast with wire brush. Wash the surface
with Pettit's Metal Primer to remove grease and dirt. Apply one
coat of Pettit's Metal Primer to bare metal and let dry four hours. Follow
with two coats of Pettit's Vinyl Red Undercoater and let dry two hours
between coats and four hours before applying two coats of Unepoxy.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS AND OUTDRIVES.

BEST DOCUMENT AVAILABLE

.....
.....
.....
.....

.....
.....
.....
.....