

# PETTIT

marine  paint

Active Ingredients  
 Cuprous Oxide 47.6%  
 Inert Ingredients 52.4%  
 100.0%

EPA Reg. No. 390-47  
 After drying overnight buff with fine bronze wool or fine wet or dry sandpaper for a super slick finish.

# UNEPOXY

ANTI FOULING  
 SUPER SLICK  
 1690 RED

## UNEPOXY COLOR:

Unepoxy is an effective hard racing antifouling boat bottom paint for various waters. It can be applied over PETTIT'S VINYLCLIDE RED and most aged non-antifouling hard racing finishes. A small test area of Unepoxy on aged hard racing finishes is recommended to determine adhesion and compatibility to the old finish. Old, soft or semi hard antifouling paints should be removed for best adhesion. Allow a minimum of 2 hours curing time between coats. After the final coat is applied, the boat may be launched after 8 hours minimum to within 2 months maximum.

**FIBERGLASS:** Wash fiberglass with PETTIT'S #12120 BRUSHING THINNER to remove parting agent, grease, and dirt. Sand thoroughly with medium grit sandpaper to dull the glossy fiberglass surface. Apply 2 coats of Unepoxy. An alternate system for fiberglass is to wash with PETTIT'S #15095 MUST DEWAXER and then apply a coat of 9399 SANDLESS PREP COAT. Do not sand the Prep Coat. Apply 2 coats of Unepoxy making sure the first coat of Unepoxy is applied to the Prep Coat within 24 hours after the Prep Coat has been applied.

**WOODEN HULLS:** Old antifouling paint should be scraped to bare wood. PETTIT'S VINYLCLIDE RED or aged non-antifouling hard racing finishes should be sanded thoroughly. If priming is necessary on bare wood, apply 1 coat of PETTIT'S RED LEAD PRIMER and let dry for 24 hours. Sand lightly and apply 2 coats of Unepoxy.

**STEEL HULLS:** To remove old rust and scale from the metal surface, scrape, sandblast, or wire brush. Wash the surface with PETTIT'S #12120 BRUSHING THINNER to remove grease and embedded dirt. Apply 1 coat of PETTIT'S VINYL METAL PRIMER to bare metal and let dry 4 hours. Follow with 2 coats of PETTIT'S VINYL RED UNDERCOATER and let dry 2 hours between coats and 4 hours before apply 2 coats of Unepoxy.

**CLEANING AND THINNING:** Use PETTIT'S #12120 BRUSHING THINNER.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS. STIR PAINT THOROUGHLY BEFORE USING.

### CAUTION

HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE SKIN IRRITATION.

CONTAINS COPPER COMPOUNDS AND AROMATIC HYDROCARBONS. Drink milk. Do not breathe spray mist. Do not get in eyes, on skin, or on clothing. May be absorbed through skin. In case of skin contact, remove contaminated clothing and immediately wash with soap and water. Wash clothes before reuse. Flush eyes with water. Get medical attention if irritation persists. Avoid storage near food or feed products. Do not apply to any surface that will be used by children. Do not reuse empty container. Destroy it by perforation or crushing. Bury or discard in a safe place. Do not use, pour, spill or store near heat or open flame. Use with adequate ventilation.

KEEP OUT OF REACH OF CHILDREN

ONE QUART U.S. STANDARD

IMPERIAL MEASURE 33 FL. OZ.

NET 32 FL.OZ.(1 QT.) CAUTION KEEP OUT OF THE REACH OF CHILDREN. OTHER PRECAUTIONS ON BACK PANEL.

PETTIT PAINT CO., INC.

BOROUGH OF ROCKAWAY  
 NEW JERSEY 07866

SAN LEANDRO  
 CALIFORNIA

JAN 4, 1973

390-47