

DEC 19, 1972
 390-48

PETTIT

marine  paint

Active Ingredients	
Cuprous Oxide	25%
Inert Ingredients	75%
	<hr/> 100%
E. P. A. Reg. No. 390-48	

ANTI-FOULING

1612
**COPPERCIDE
 RED**

UNDER
 FUNGICIDE
 FOR ECONOM
 ED UNDER NO.

NET 32 FL.OZ.(1QT.) **CAUTION** KEEP OUT OF THE REACH OF CHILDREN.
 OTHER PRECAUTIONS ON BACK PANEL.

PETTIT PAINT CO., INC.

PETTIT COPPERCIDE ANTI-FOULING PAINT

A new formulation of copper anti-fouling paint for protection of wooden, steel and fiberglass boat bottoms.

DIRECTIONS

Stir paint thoroughly before starting and keep stirred during use. The bottom to be painted should be as dry as practical. The old paint should be scrubbed or scraped off as thoroughly as possible. The boat should be launched within 8 to 24 hours after the final coat is applied. Allow an overnight dry between coats.

WOODEN HULLS: Do not use a primer. Apply COPPERCIDE directly to wood, reducing first coat over bare wood 10% with PETTIT 120 THINNER. On repaint work apply two coats without reduction.

STEEL & ALUMINUM: Apply one coat of PETTIT METAL PRIMER. Then apply two coats of PETTIT VINYL RED UNDERCOATER. Scuff sand the last coat before applying two coats of COPPERCIDE.

FIBREGLASS: Apply one coat of PETTIT FIBREGLASS UNDERCOATER as directed followed by two coats of COPPERCIDE.

CAUTION

HARMFUL OR FATAL IF SWALLOWED

CONTAINS COPPER AND PETROLEUM DISTILLATE. DO NOT INDUCE VOMITING. Do not apply on window sills, toys, furniture, or interior surfaces which may be used by children. Avoid prolonged contact with skin and breathing vapor or spray mist. Wash thoroughly after handling and before eating or smoking. Do not use, pour, spill or store near heat or open flame. Do not reuse container. Destroy when empty. Close container after each use.

Use with adequate ventilation. **KEEP OUT OF THE REACH OF CHILDREN.**

ONE QUART U.S. STANDARD

IMPERIAL MEASURE 33 FL. OZ.

BOROUGH OF ROCKAWAY, N.J. 07866 - SAN LEANDRO, CALIF. 94577