

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND
DOMESTIC ANIMALS
WARNING

KEEP OUT OF REACH OF CHILDREN
Use only with
adequate ventilation

Harmful if swallowed. Avoid contact with
skin and breathing of vapor or spray mist.
Causes eye and skin irritation.

FIRST AID: In case of contact, im-
mediately flush eyes or skin with
plenty of water for at least 15 min-
utes. For eyes, call a physician. If
inhaled remove to fresh air. Remove
and wash contaminated clothing be-
fore reuse. Wash thoroughly with soap
and water after handling and before
eating and smoking.

If swallowed, drink promptly a large
quantity of milk, egg whites, gelatin
solution or if these are not available,
drink large quantities of water. Never
give anything by mouth to an uncon-
scious person. Avoid alcohol. Call a
physician immediately.

ENVIRONMENTAL HAZARD
Do not contaminate water by cleaning
of equipment or disposal of wastes.

PHYSICAL OR CHEMICAL HAZARD
COMBUSTIBLE! Do not use or store near
heat or open flame.

(continued on right hand panel)

32 FL.OZ. (1 QT.) 946 mL

WARNING! KEEP OUT OF REACH OF CHILDREN.
COMBUSTIBLE. OTHER PRECAUTIONS ON SIDE PANEL.

PETTIT

marine paint

UNEPOXY

ANTI FOULING

**1522 BROWN
ATLANTIC FORMULA**

ACCEPTED
1981



ACTIVE INGREDIENTS
Cuprous Oxide 22.0
Methylene Blue 47.4
INERT INGREDIENTS 100.0

(continued from left hand panel)

DIRECTIONS FOR USE

It is a violation of federal law to use
this product in a manner inconsistent
with its labeling.

NOTE—Wear protective clothing when
product is used in confined areas or ap-
plied by spraying, wear a respirator jointly
approved by the Mining Enforcement and
Safety Administration (formerly the U.S.
Bureau of Mines) and by the National
Institute for Occupational Safety and Health
under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

Unepoxy is an anti-fouling protective
coating resistant to algae, barnacles
and other marine fouling.

STORAGE & DISPOSAL

Do not contaminate water, food, or
feed by storage or disposal. Open
dumping is prohibited.

Pesticide, spray mixture, or rinsate that
cannot be used or chemically reprocessed
should be disposed of according to proce-
dures approved by Federal, State, or local
disposal authorities.

Container—Triple rinse (or equivalent)
and dispose of in an approved landfill or
bury in a safe place. Consult Federal, State,
or local disposal authorities for approved
alternative procedures.

E.P.A. REG. NO.390-56
E.P.A. EST. NO.390-NJ-1

UNEPOXY ANTIFOULING

PRODUCT DESCRIPTION: Unepoxy is an effective, hard-facing, antifouling boat bottom paint for various waters. It can be applied over vinyl and other hard antifouling paints if these are in good condition. Old soft or semi-hard antifouling paints should be thoroughly sanded or removed for best adhesion.

PREPARATION OF SURFACE: The surface to be painted should be dry, clean, and oil-free. It should be properly prepared by solvent cleaning and/or sanding before any primers or paints are applied. Follow the recommended systems below.

APPLICATION AND TEMPERATURE: Unepoxy can be applied by brush, roller, or spray. The work should be done between 9:00 A.M. and 4:00 P.M. under good drying conditions. The temperature range of application is 40° to 90° F. Two coats should always be applied for best antifouling protection.

PREPARATION OF PAINT: Unepoxy is heavily loaded with cuprous oxide. As a result of this loading there is a tendency for settling to occur especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible shake the can of paint on a mechanical paint shaker. Before using check the sides and bottom of the can to make sure all the pigment has been grinded in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment; then remix the two parts together thoroughly.

THINNER: Use Pettit's 12120 Brushing Thinner for thinning the Unepoxy on a warm wind, day or for cleaning up equipment. Do not over thin Unepoxy or inadequate paint application will occur.

DRY TIMES: Let the first coat of Unepoxy dry between two to four hours minimum before applying the second coat. After the second coat is applied, let the paint dry at least eight hours or preferably overnight before immersing the boat. Under adverse drying conditions let the boat dry overnight to make sure all the solvent is out of the paint film. Maximum immersion time is two months.

COVERAGE: Unepoxy covers approximately 400 square feet per gallon.

MAINTENANCE OF ANTIFOULING PAINT: No antifouling paint can be effective under all conditions of exposure. Manmade pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water, and some electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked several times a month to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

PAINT SYSTEMS

FIBERGLASS: Wash the fiberglass with Pettit's 12120 Brushing Thinner or 15095 Dewaxer to remove parking agent, grease, and dirt. Sand thoroughly with 80-120 grit sandpaper to dull the glossy fiberglass surface. Rewash the sanded surface and then apply two coats of Unepoxy. To skip the sanding operation after the hull has been washed, apply a coat of Pettit's 6004 Skip Sand primer. Then apply two coats of Unepoxy.

BLISTERED GELCOTE: Remove all antifouling paint by sanding or using Pettit's 9030 Fiberglass Paint & Varnish Remover. Sand the gelcote and fill any voids with Pettit's 7190 Polyester Mender. Sand smooth, apply a coat of Pettit's 4169 Polyepoxy Undercoater / 4027 Polyepoxy Brush Hardener. Let dry 24 hours minimum, sand lightly and then apply two coats of Unepoxy.

WOODEN HULLS: Old antifouling paint should be thoroughly sanded or scraped to bare wood. If priming is necessary on bare wood, apply one coat of Pettit's Red Lead Primer and let dry for 24 hours. Sand lightly and apply two coats of Unepoxy.

STEEL HULLS/UNDERWATER METAL PARTS: To remove old rust and scale from the metal surface scrape or sandblast with wire brush. Wash the surface with Pettit's 12120 Brushing Thinner to remove grease and dirt. Apply one coat of Pettit's Metal Primer to bare metal and let dry four hours. Follow with two coats of Pettit's Vinyl Red Undercoater and let dry two hours between coats and four hours before applying two coats of Unepoxy.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS AND OUTDRIVES.

50-192

PETTIT PAINT CO., INC.

BOUGH OF ROCKAWAY, N.J. 07866 - SAN LEANDRO, CALIF. 94577

390-56

2/2/1981

Page 131