

PETTIT

marine paint



ANTI-FOULING

1641
CHESAPEAKE
RED COPPER

COPPER AS METALLIC... 17.8%

This product contains petroleum distillates

390-57

1 GALLON 3.785 LITERS

WARNING! KEEP OUT OF REACH OF CHILDREN.
COMBUSTIBLE. SEE SIDE PANEL FOR
ADDITIONAL PRECAUTIONARY STATEMENTS.

PETTIT PAINT CO., INC.

CHESAPEAKE RED COPPER

PRODUCT DESCRIPTION: Chesapeake Red Copper is manufactured as an effective antifouling paint for use on fishing boats and trawlers used in the Chesapeake area. It can be applied over old, soft or hard antifouling paints that are in good condition.

PREPARATION OF SURFACE: The surface to be painted should be dry, clean, and oil free. It should be properly prepared by solvent cleaning and/or sanding before any primers or paints are applied. Follow the recommended systems below.

APPLICATION AND TEMPERATURE: Chesapeake Red Copper can be applied by brush, roller, or spray. The work should be done between 9:00 A.M. and 4:00 P.M. under good drying conditions. The temperature range of application is 40° to 90° F. Two coats should always be applied for best antifouling protection.

PREPARATION OF PAINT: Chesapeake Red Copper contains cuprous oxide, a heavy pigment. As a result of using this product, there is a tendency for settling to occur especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible shake the can of paint on a mechanical paint shaker. Before using check the sides and bottom of the can to make sure all the pigment has been mixed in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment; then remix the two parts together thoroughly.

THINNER: Use Pettit's 12120 Brushing Thinner or Mineral Spirits for thinning the paint on a warm windy day or for cleaning up equipment.

DRY TIMES: Let the first coat of Chesapeake Red Copper dry six hours to overnight before the second coat is applied. After the second coat is applied, immerse the boat within 48 hours.

COVERAGE: Chesapeake Red Copper covers approximately 400 square feet per gallon.

MAINTENANCE OF ANTIFOULING PAINT: No antifouling paint can be effective under all conditions of exposure. Man-made pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water, and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked several times a month to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

WOODEN HULLS: Scrape or sand off any loose paint. Prime all bare wood with Pettit Red Lead Primer or Chesapeake Red Copper thinned 50% with one of our recommended thinners. After the prime coat has dried, apply two coats of paint.

STEEL HULLS: Wire wheel or lightly sandblast any loose scale, rust or old paint. Apply two coats of Pettit's 6980 BuSt Lok Steel Primer to any bare steel. After the second coat dries approximately two hours, apply the first of two coats of the Chesapeake Red Copper.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS AND OUTDRIVES.

BOROUGH OF ROCKAWAY, N.J. 07866 - SPRING VALLEY, CALIF. 92077

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS
WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe sanding dust, vapor or spray mist. While spraying or sanding any flume surface, wear a mask or respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

If swallowed: Drink promptly a large quantity of milk, egg whites, gelatin solution or, if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention.

If in eyes: Flush with plenty of water. Get medical attention.

If on skin: Wash with plenty of soap and water. Get medical attention.

If inhaled: Remove victim to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Get medical attention.


ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARD

COMBUSTIBLE! Do not use or store near heat or open flame

(continued on right hand panel)



(continued from left hand panel)

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

NOTE - When product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

Chesapeake Red Copper is an anti-fouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE & DISPOSAL

Pesticide, spray mixture, or rinsate that cannot be used according to label instructions must be disposed of according to Federal or approved state procedures under Subtitle C of the Resource Conservation and Recovery Act.

Container Disposal

Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other approved state and local procedures.

E.P.A. REG. NO..... 390-57
E.P.A. EST. NO..... 390-NJ-1