

REST ASSURED COPY 1

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

DANGER

KEEP OUT OF REACH OF CHILDREN

Use only with adequate ventilation.
CORROSIVE Causes severe skin and eye damage. Do not get on skin, clothing or in eyes. Wear a face shield and rubber gloves when handling. Use in a well ventilated area. Harmful if swallowed or inhaled. Do not breathe vapors or spray mist.

PRACTICAL TREATMENT In case of skin contact remove contaminated clothing and immediately wash skin with soap and water. Get medical attention. Wash contaminated clothing before reuse. If inhaled remove to fresh air. Use artificial respiration if breathing has stopped. Get immediate medical attention. If swallowed do not induce vomiting. This product contains petroleum distillates. Get immediate medical attention. If in eyes, flush eyes with water. Get medical attention.


ENVIRONMENTAL HAZARD

This product is toxic to fish and wildlife. Do not contaminate water by cleaning equipment or disposal of waste. Do not apply directly to water.

PHYSICAL OR CHEMICAL HAZARD

COMBUSTIBLE! Do not use or store near heat or open flame.

(continued on right hand page)

PETTIT
marine 

HOE

ANTIF
FORME

ACCEPTED
7380

8 GREEN

Federal Insecticide
and Rodenticide Act
Registered under
EPA No. 390-59

DANGER

1 QUART

PETTIT PAINT CO.

1074

(continued from left hand panel)

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

NOTE — When product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

HORIZONS is an anti-fouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE & DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Pesticide paint or rinsate that cannot be used according to label instructions must be disposed of according to federal, state or local procedures under the Resource Conservation and Recovery Act.

Container Disposal: triple rinse (or equivalent) and offer for recycling or reconditioning or disposal in a sanitary landfill or by other approved state and local procedures.

EPA REG. NO.
EPA EST. NO.

390-59
390-NJ-1

HORIZONS ANTIFOULING

Horizons is a Pettit marine antifouling paint designed to protect boat bottoms from barnacles, algae and other marine growth. Both the resinous binder and cuprous oxide give Horizons its antifouling qualities. This principle provides continuous antifouling "spots" on the paint surface at all times. The paint surface also slowly erodes away while the boat is being used, giving a slick, smooth finish at all times. Horizons can be applied over Pettit's aged Unipoxy or Trinidad or other hard antifouling paints. Old soft and semi-hard antifouling paints should not be coated with Horizons. Remove them and follow the proper system listed below.

PREPARATION OF SURFACE: The surface to be painted should be dry, clean and oil-free. It should be properly prepared by solvent cleaning and/or sanding before any primers or paints are applied. Follow the recommended systems below. When sanding old antifouling paint, use a face mask to prevent the inhalation of sanding dust.

APPLICATION AND TEMPERATURE: Horizons can be applied by brush, roller or spray. The work should be done between 9:00 A.M. and 4:00 P.M. under good drying conditions. The temperature range of application is between 55° and 90° F. At least two and preferably three or four coats should be applied for best antifouling protection. Extra coats of Horizons should be applied to high wear areas and the waterline.

PREPARATION OF PAINT: Horizons contains cuprous oxide. As a result, there is a tendency for setting to occur, especially if the paint has been on the shelf several months. It is necessary to thoroughly mix the paint before using. If possible, shake the can of paint on a mechanical paint shaker. Before using, check the sides and bottom of the can to make sure all the pigment has been mixed in. If mixing is going to be done with a wooden paddle or electric drill mixer, pour off half the liquid from the top of the can and then properly mix in any settled pigment; then remix the two parts together thoroughly.

THINNING: Use Pettit's 12120 Brushing Thinner for thinning Horizons on a warm windy day or cleaning up equipment. Do not over thin Horizons. Otherwise inadequate paint application will occur.

DRY TIME: Let each coat of Horizons dry four hours minimum before applying the next coat. After the final coat is applied, let the paint dry at least eight hours or, preferably, overnight before launching the boat. Under adverse conditions let the boat dry overnight to make sure all solvent is out of the paint film.

COVERAGE: Horizons covers approximately 400 square feet per gallon.

MAINTENANCE OF ANTIFOULING PAINT: No antifouling paint can be effective under all conditions or exposure. Man-made pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, salt, dirt, or brackish water, and even electrolysis can turn an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked periodically to make sure it is clean.

PAINT SYSTEMS

FIBERGLASS: Wash the fiberglass with Pettit's 12120 Brushing Thinner or 5095 Detergent to remove parting agents, grease and dirt. Sand thoroughly with 80 grit sandpaper to dull the glossy fiberglass surface. Remove the sanded surface and then apply at least two coats of Horizons to paint over hard antifouling paint. Lightly sand the painted surface before applying a second antifouling paint.

WETTED SURFACES: Remove an antifouling paint by sanding or using Pettit's 9030 Fiberglass Paint & Epoxy Resin. Sand the entire surface and then sand with 80 grit sandpaper to dull the glossy surface. Remove the sanded surface and then apply at least two coats of Pettit's 4169 Polyurethane Undercoat. Prepare brush thoroughly in advance. Mix thoroughly and thoroughly sand the entire surface with 80 grit sandpaper and then apply the resin antifouling paint.

WETTED SURFACES: Remove an antifouling paint by sanding or using Pettit's 9030 Fiberglass Paint & Epoxy Resin. Sand the entire surface and then sand with 80 grit sandpaper to dull the glossy surface. Remove the sanded surface and then apply at least two coats of Pettit's 4169 Polyurethane Undercoat. Prepare brush thoroughly in advance. Mix thoroughly and thoroughly sand the entire surface with 80 grit sandpaper and then apply the resin antifouling paint.

TRIM: Use Pettit's 4169 Polyurethane Undercoat. Prepare brush thoroughly in advance. Mix thoroughly and thoroughly sand the entire surface with 80 grit sandpaper and then apply the resin antifouling paint.

WOOD: Use Pettit's 4169 Polyurethane Undercoat. Prepare brush thoroughly in advance. Mix thoroughly and thoroughly sand the entire surface with 80 grit sandpaper and then apply the resin antifouling paint.

PETTIT PAINT COMPANY, INC.

1000 W. 10TH AVE., DENVER, CO. 80202