

578-6

1-20-1948

1/2

5 U. S. GALLONS

**CLEAR**

**#20**

**CUPRINOL®**

**WOOD  
PRESERVATIVE**

ACCEPTED

1-20-48

578-6

**FUNGUS GROWTH  
DRY ROT  
WOOD BORERS\*  
MILDEW  
MARINE GROWTHS\***

\* See side panels for details

ACTIVE INGREDIENTS

ZINC NAPHTHENATE 38%

EQUIVALENT TO METALLIC ZINC 4%

INERT INGREDIENTS 62%

TOTAL 100%

CONTAINS NO COPPER

CUPRINOL DIVISION, DARWORTH, INC., SIMSBURY, CONNECTICUT

15-1A-1

## CUPRINOL WOOD PRESERVATIVE CLEAR NO. 20

CUPRINOL prolongs the life of wood by preventing rot and damage from termites also teredo and gribble. It retards as well fouling by barnacles and marine vegetable growths.

This grade is for use over stains or where surfaces are to be left a natural wood finish.

Treated wood after drying twenty-four hours is non-toxic to plant or animal life.

### COVERAGE

One gallon will cover 250 to 600 square feet (not board feet) depending on the porosity of wood and roughness of surfaces.

### DIRECTIONS FOR USE

Content of the container is ready for use after stirring and should not be diluted. Apply by brushing, spraying or dipping and no protective clothing is required unless the user is allergic to petroleum distillates.

Paint, varnish, wax or other films and all layers of bark must be removed before applying CUPRINOL. Moisture in wood reduces penetration, therefore, the drier the wood the more effective the treatment.

CUPRINOL will not stop knots or stains from bleeding through paint. Use shellac after CUPRINOL.

All newly exposed surfaces resulting from cutting, sanding or boring of treated wood should be treated with CUPRINOL. If more than one coat of CUPRINOL is used apply additional coat before first coat is dry, (within ten minutes). It may replace the priming coat if three coats of paint are planned.

Allow a minimum of twenty-four hours drying time before finishing with paint or other coating material.

Keep container tightly closed to stop evaporation.

Clean CUPRINOL from hands, brushes, containers or other surfaces with kerosene, white gasoline or carbon tetrachloride.

### CAUTION — FLAMMABLE MIXTURE

The solvent used in CUPRINOL has a flash point of 105° F.

Do not smoke or use near open flame.

Use in a well ventilated place.

Note — CUPRINOL does not increase the flammability of wood when treated as the solvent entirely evaporates.

Under copper bottom paint, use CUPRINOL Green No. 10. Do not use this grade.

There are other types of CUPRINOL for fabric, rope and nets.

For information ask your dealer or write the company.

CUPRINOL DIVISION, DARWORTH, INC., SIMSBURY, CONNECTICUT

ACCEPTED  
1-20-48  
518-8