



**AMSCO'S**

**CREOSOTE**

**WOOD PRESERVER**

**ACTIVE INGREDIENTS**

Coal Tar Creosote 97% Min.

**INERT INGREDIENTS**

Water 3% Max.

**ONE U.S. GALLON**

**ACCEPTED**

MAY 25 1971

UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC POISON REGISTERED  
ED UNDER NO. 528-29

**WARNING!**

**HARMFUL OR FATAL IF SWALLOWED  
KEEP OUT OF REACH OF CHILDREN**

See cautions on back panel

DISTRIBUTED BY

**AMERICAN MINERAL SPIRITS COMPANY**  
A Division of Union Oil Company of California  
Minneapolis, Minnesota 55414

21201	SHERWIN-WILLIAMS CO.
AMSCO'S	CREOSOTE
GAL "F" 15.	CE 9.562" 20.260"
PRT. YELLOW • BROWN ON WHITE	
5890	3-18-71



# CREOSOTE

A refined Coal Tar Creosote Oil that protects wood from ground moisture and resists attack of insects and fungi or rot. It will add greatly to the life of fence posts, telephone poles, timbers, sills, joints, etc. when properly applied.

## DIRECTIONS

Apply Amisco's Creosote Wood Preserver by dipping, brushing or spraying. One gallon will cover an area of approximately 100 square feet. For proper treatment, wood should be free of bark, dry and well seasoned. When treated by the dip method, wood should be immersed for 12 to 48 hours into the cold or heated solution. For maximum penetration, when applying in cold weather, heat Creosote to 150°F. For wood which is to be in contact with the soil, apply two coats thoroughly by brush or spray method. For wood to be painted, use Amisco Pentachlorophenol Wood Preserver.

## WARNING

Avoid contact with skin and clothing as it may cause skin irritation. Do not store or use near heat or open flame. Avoid breathing vapors or spray mist. Do not take internally. Harmful if swallowed.

Use with adequate ventilation.

U.S.D.A. Reg. No. 52-114

MADE IN U.S.A.

STOMER

*[Small, faint text block, likely bleed-through from the reverse side of the page]*

*[Small, faint text block, likely bleed-through from the reverse side of the page]*