

ONE U.S. GALLON



**1-5 CONCENTRATE WATER REPELLENT
WOOD PRESERVER**

ACTIVE INGREDIENTS

* Pentachlorophenol	21.76%
* Other Chlorophenols & related compounds	2.53%
Petroleum Distillate	30.70%
INERT INGREDIENTS	
Water repellents & Special Solvents	45.01%

*Contains 25.3% of Technical Pentachlorophenol as defined in Federal Specification 11-W-570

ACCEPTED
AUG 3 1970

DANGER! COMBUSTIBLE
HARMFUL OR FATAL IF SWALLOWED
KEEP OUT OF REACH OF CHILDREN
See Caution on back panel

DISTRIBUTED BY
AMERICAN MINERAL SPIRITS COMPANY
Division of The Pure Oil Company
Minneapolis, Minnesota

ACCEPTED

UNDER THE FEDERAL INSECT
FUNGICIDE AND ROYALTY ACT
FOR ECONOMIC POISON CONTROL
ED UNDER NO. 528-51
TO ATTACHED COMMENTS



PENTA SEAL CONCENTRATE 1-5

USES: A water repellent wood preserver for treatment of millwork, plywood, furniture, cabinet work, doors, interior trim and panels, and wood specialty products—for control of decay, termites, blue stain, and dimensional changes such as swelling, warping, shrinking, and checking resulting from changes in moisture content.

MIXING INSTRUCTIONS: For ready to use 5% solution, mix one part of Penta Seal Concentrate with 5 parts by volume of Mineral Spirits or Range Oil. In cold weather, warm the Concentrate before mixing.

APPLICATION (Diluted Ready to Use solution): Dipping—For most effective treatment, immerse wood in the solution for a minimum of 3 minutes.

Brushing—Two applications recommended. On end grain make several extra applications.

COVERAGE (Ready to Use solution): Dipping—5 to 10 gallons per 1000 board feet. Brushing—1 gallon of solution per 200 square feet.

DIRECTIONS FOR USE (Ready to Use solution): Penta Seal generally is applied by dipping wood in the solution for a minimum period of 3 minutes. Although where dipping is impractical, a heavy brush application may be applied. Where wood is to be in contact with the soil, at least two heavy brush applications are recommended. Penta treated surfaces will dry to touch in 2 to 4 hours and may be painted over in 2 or 3 days leaving no residue to bleed through and prevent painting of treated surface. Penta treated wood is compatible with paint and varnish. It meets all requirements for millwork treatment standards of National Woodwork Manufacturers Assn. and many Government Specifications.

Insofar as possible, the millwork, lumber or plywood should be fabricated prior to treatment. Whenever it is necessary to do some cutting of the wood after treatment, the exposed surfaces should be re-dipped or given several brush coats of Penta Seal Ready to Use.

For protection against termites, treat wood prior to use in construction.

CAUTION! Harmful if swallowed or absorbed through skin! Causes skin irritation. Keep out of eyes. Remove clothing that has become soaked with Penta solution.

Do not breathe vapors or spray mist.

Do not use near fire or open flame.

Keep container closed.

Use with adequate ventilation.

ANTIDOTE: External—wash with rubbing alcohol and follow with soap and water. In case of contact with eyes, flush liberally with water for at least 15 minutes.

Internal—Call a physician immediately. Give a tablespoon of salt in a glass of warm water and repeat until vomit fluid is clear. Give milk or white of egg beater, with water. Have patient lie down and keep warm.

U.S.D.A. registration No. 528-51

MADE IN U.S.A.