

Sears MARINE



**ANTI-FOULING
BOTTOM PAINT**

 with TBTF for salt or fresh water

FORMULA • 6365
GOLD BRONZE
 PIGMENT 20.43%
 Copper Bronze
 Powder 14.3%
 (70% Copper)
 VEHICLE 79.6%
 Tri-n-butyltin
 Fluoride
 Resin
 Solvent
 Tri-n-butyltin
 Fluoride

EPA REG. NO. 539-270-AA
 EPA EST. NO. 8788-TX-1

⚠ DANGER
 May cause severe eye burns. May cause eye damage. May be fatal if swallowed. May cause skin irritation or delayed chemical burns. Do not get in eyes, on skin, or on clothing. Combustible! Vapor harmful, avoid breathing of vapor, spray mist, or sanding dust. Keep away from heat, sparks and open flame. Use with adequate ventilation. Close container after each use. Do not reuse empty container. Destroy it by perforating or crushing. Bury or discard in a safe place.

ANTIDOTE STATEMENT
 In case of contact, immediately flush eyes with plenty of water for at least 15 minutes and get medical attention. Wash skin with plenty of soap and water. Wash contaminated clothing before re-use. If swallowed CALL PHYSICIAN IMMEDIATELY.

GOLD BRONZE
 32 63654
32 FL. OZ. (1 QT.)
DANGER!
 See side for other warnings.
KEEP OUT OF REACH OF CHILDREN

*Active Ingredients
 Tri-n-butyltin
 Fluoride 9.2%
 Copper Powder 14.3%
 Inert Ingredients 77.5%
 (Metallic Tin 3.15%)

WETTING SPRAY
 Use with MARINE ANTI-FOULING PAINT. Apply with TBTF. For DANGER! See TBTF. See MARINE ANTI-FOULING PAINT. Recommended for use with MARINE ANTI-FOULING PAINT.

FEATURES
 • Easy to use
 • No mixing
 • No sanding
 • No priming
 • No painting

BEFORE USING
 Read the directions on the label. Do not use if the label is missing or if the product is not in its original container. Do not use if the product is not in its original container. Do not use if the product is not in its original container.

This product is not for use on...
 Do not use on...
 Do not use on...

Do not use on...
 Do not use on...
 Do not use on...

Do not use on...
 Do not use on...
 Do not use on...

APPLICATION
 Apply with TBTF. Do not use if the label is missing or if the product is not in its original container. Do not use if the product is not in its original container. Do not use if the product is not in its original container.

NOTE: Scratches and gouges that penetrate the paint damage from corrosion or galvanic action. Send damage directions for painting metals.
COVERAGE: Approximately 100 sq. ft. (9 sq. meters) per quart.
 Sold by SEARS, ROEBUCK AND CO.

Aug. 7, 1974
57-120
339-270
PTED
MARINE



ANTI-FOULING BOTTOM PAINT

with TBTF for salt or fresh water

FORMULA - 6365
GOLD BRONZE
Pigment 28.4%
*Copper Bronze
Powder (70% Copper) 100.0%
VEHICLE 79.6%
Acrylic Polyester Resin 25.6
Xylol 64.2
*Tri-n-butyltin Fluoride 10.2
100.0%

EPA REG. NO. 539-270 AA
EPA EST. NO. 8788-TX-1

GOLD BRONZE
28 63654

32 FL. OZ. (1 QT.)

DANGER!

See side for other warnings.

KEEP OUT OF REACH OF CHILDREN

*Active Ingredients
Tri-n-butyltin Fluoride 8.2%
Copper Powder 14.2
Inert Ingredients 77.5
100.0%
(Metallic Tin 2.15%)

DO NOT SPRAY!
WEAR MASK WHILE SANDING TO AVOID BREATHING PAINT DUST. THE SPECIAL WATER RESISTANT ACRYLIC RESINS IN COMBINATION WITH TBTF PROVIDE EFFECTIVE PROTECTION AGAINST BARNACLES, TEREDOS, ALGAE, AND OTHER MARINE FOULING ORGANISMS.

RECOMMENDED FOR: All wood, plywood, fiberglass and properly primed metal boats.

FEATURES:

- TBTF (tri-n-butyltin fluoride) has been proven a most effective anti-fouling toxicant.
- The water-resistant acrylic base develops a hard, medium-gloss finish, yet allows proper release of TBTF to retard any growth or attachment.
- Formulated in "fade resistant", rich, bright colors.
- TBTF remains effective . . . even if boat is pulled from water and relaunched frequently.

DIRECTIONS

BEFORE YOU PAINT:

Surface should be clean and sound. Check adhesion of old paint with a knife blade before painting over previously painted surfaces. If old paint lifts easily or is in generally poor condition it should be removed. Previous coats of "soft" or "semi-hard" bottom paints, identifiable by a chalky or powdery feel, should be completely removed. Use Sears PAINT and VARNISH REMOVER (except on fiberglass) or power sanding to remove old paint.

OLD PAINT IN GOOD CONDITION:

Sand thoroughly to remove gloss, then wipe with Sears EPOXY and LACQUER THINNER or SAND BAN. Apply two or three finish coats unthinned.

NEW OR UNFINISHED WOOD:

Sand thoroughly, caulk seams and cracks. Apply first coat thinned 25% with Sears TIRPOLENE™ and allow to dry several hours. Sand lightly before applying two or three finish coats unthinned.

FIBERGLASS:

Sand thoroughly to remove gloss. Wash surface with Sears EPOXY and LACQUER THINNER to remove grease, wax, and mold release agent. Apply two or three finish coats unthinned.

METALS (Steel and Aluminum)

Preparation of metal below the water line is extremely critical. Complete insulation from water is necessary to prevent pitting and other permanent damage. Remove all rust and corrosion with steel wool or by sanding until the metal is bright. Sand pit marks smooth. Finish sand with very fine emery cloth, to remove protruding metal slivers. Wash surface with Sears EPOXY and LACQUER THINNER or SAND-BAN to remove traces of oil, grease or wax. Prime with Sears MARINE METAL PRIMER following the instructions given on the label of that product. Apply two or three finish coats unthinned.

APPLICATION:

For boats used in fresh water, apply a minimum of two coats of Sears ANTI FOULING BOTTOM PAINT. At least three coats should be used on boats used in salt water. For best results, avoid painting in direct sunlight. Stir paint thoroughly before and during application. Flow on paint generously with good quality natural bristle brush or enamel roller. Allow at least four hours drying time between coats. Allow at least forty-eight hours after application of last coat before boat is launched. Clean brushes and other tools with Sears TIRPOLENE or EPOXY and LACQUER THINNER immediately after using.

NOTE: Scratches and gouges that penetrate the paint to bare metal should be repaired to avoid damage from corrosion or "galvanic action." Sand damaged areas to bare metal and follow above directions for painting metals.

COVERAGE: Approximately 100 sq. ft. (1 sq. meter) per quart.

Sold by SEARS, ROEBUCK AND CO., Chicago, IL 60684