

MARINE



Sears + Best

ANTI-FOULING BOTTOM PAINT

with TBTF for salt or fresh water

ACCEPTED

30 Red

EPA REG. NO. 539 275
EPA EST. NO. 8788 IL 1

Active Ingredients
Tributyltin Fluoride 8.1
Inert Ingredients 91.9
Metallic Tin 1.1 100.0

**KEEP OUT OF THE REACH OF CHILDREN.
DANGER**

See Side Panel for Additional Precautionary Statements

PRECAUTIONARY STATEMENTS DANGER: HAZARDS TO HUMANS AND DOMESTIC ANIMALS

Corrosive Causes irreversible eye damage and burns. Harmful if absorbed through skin. Swallowed or inhaled. Do not get on skin, eyes, or clothing. Wear goggles or safety glasses. Wear protective clothing such as long sleeved cotton shirt, long pants, hat and gloves. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash before reuse. Avoid breathing vapor, dust or chips from sanding. Use with adequate ventilation. Close container after each use.

FIRST AID STATEMENT

If swallowed: Drink promptly a large quantity of milk, egg whites, gelatin solution or if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention.

NOTE TO PHYSICIAN: Probably mucosal damage may contraindicate the use of gastric lavage.

If in eyes: Flush with plenty of water. Get medical attention.

If on skin: Wash with plenty of soap and water. Get medical attention.

ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARDS

COMBUSTIBLE Do not use or store near heat, sparks or open flame. Use with adequate ventilation. **NOTE:** While spraying and/or sanding boat surface wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and by the National Institute for Occupational Safety and Health.

DIRECTIONS FOR USE: IT IS A VIOLATION OF FEDERAL LAW TO USE THIS PRODUCT IN A MANNER INCONSISTENT WITH ITS LABELING.

STORAGE AND DISPOSAL

Do not reuse empty container. Wrap container and put in trash collection.

Keep out of reach of children

ALL WOOD, PLYWOOD
THE SPECIAL WATER-RESISTANT
EFFECTIVE PROTECTION AGAINST
ING ORGANISMS

• TBTF (Tributyltin Fluoride)
resistant acrylic base does not
retard mold growth or attack
remains effective even

DO NOT SPRAY! WEAR MASK
BEFORE YOU PAINT. Smooth
blade before painting over old
condition it should be re-
by a chisel or powder.

REMOVER (except on for-
OLD PAINT IN GOOD COND-
and LACQUER THINNER-A-
NEW OR UNFINISHED WOOD

25% with Sears EPOXY
applying two or three

FIBERGLASS. Sand then
THINNER to remove grease.

METALS (Steel and Alu-
Complete insulation from

Remove all rust and cor-
smooth. Finish sand with

with Sears EPOXY and
MARINE METAL PRIMER

three finish coats with

For boats used in fresh

PAINT. At least three

painting in direct sun-
generously with good qu-

time between coats. A-
launched. Clean brush

after using.

NOTE: scratches and
damage from corrosion

directions for painting
COVERAGE: Approximate

Sold

30 63614 RED

32 FL. OZ. (1 QT.)

LARINE



ANTI-FOULING BOTTOM PAINT

with TBTF for salt or fresh water

PRECAUTIONARY STATEMENTS
DANGER: HAZARDS TO HUMANS and DOMESTIC ANIMALS
Corrosive: Causes irreversible eye damage and burns. Harmful if absorbed through skin, swallowed or inhaled. Do not get on skin, in eyes, or on clothing. Wear goggles or safety glasses. Wear protective clothing such as long sleeved cotton shirt and pants, hat and gloves. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash before reuse. Avoid breathing vapor. Dust or chips from sanding use with adequate ventilation. Close container after each use.
FIRST AID STATEMENT
If swallowed: Drink promptly a large quantity of milk, egg whites, gelatin solution or if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention.
NOTE TO PHYSICIAN: Probably mucous membrane damage may contraindicate the use of gastric lavage.
If in eyes: Flush with plenty of water. Get medical attention.
If on skin: Wash with plenty of soap and water. Get medical attention.
ENVIRONMENTAL HAZARDS
This material is toxic to fish. Do not apply directly to water by cleaning of equipment and disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.
PHYSICAL OR CHEMICAL HAZARDS
COMBUSTIBLE: Do not use or store near heat, sparks or open flame. Use with adequate ventilation. **NOTE:** While spraying and sanding boat surface wear a mask and respirator (only approved by the Mining Enforcement and Safety Administration and by the National Institute for Occupational Safety and Health).
DIRECTIONS FOR USE: IT IS A VIOLATION OF FEDERAL LAW TO USE THIS PRODUCT IN A MANNER INCONSISTENT WITH ITS LABELING
STORAGE AND DISPOSAL
Do not reuse empty container. Wrap container and put in trash collection. Keep out of reach of children.

RECOMMENDED FOR
ALL WOOD, PLYWOOD, FIBERGLASS AND PROPERLY PRIMED METAL BOATS
THE SPECIAL WATER RESISTANT ACRYLIC RESINS IN COMBINATION WITH TBTF PROVIDE EFFECTIVE PROTECTION AGAINST BARNACLES, TEREDOS, ALGAE AND OTHER MARINE FOULING ORGANISMS.

FEATURES
• TBTF (Tributyltin Fluoride) has been proven a most effective anti-fouling toxicant. • The water resistant acrylic base develops a hard, medium gloss finish, yet allows proper release of TBTF to retard most growth or attachment. • Formulated in "fade resistant" rich, bright colors. • TBTF remains effective even if boat is pulled from water and relaunched frequently.

DIRECTIONS FOR USE
DO NOT SPRAY! WEAR MASK WHILE SANDING TO AVOID BREATHING PAINT DUST
BEFORE YOU PAINT: Surface should be clean and sound. Check adhesion of old paint with a knife blade before painting over previously painted surfaces. If old paint lifts easily, it is in generally poor condition and should be removed. Previous coats of soft or semi-hard bottom paints identifiable by a chalky or powdery feel should be completely removed. Use SEARS PAINT AND VARNISH REMOVER (except on fiberglass) or power sanding to remove old paint.

OLD PAINT IN GOOD CONDITION: Sand thoroughly to remove gloss, then wipe with SEARS EPOXY and LACQUER THINNER. Apply two or three finish coats unthinned.

NEW OR UNFINISHED WOOD: Sand thoroughly, caulk seams and cracks. Apply first coat thinned 25% with SEARS EPOXY and LACQUER THINNER and allow to dry several hours. Sand lightly before applying two or three finish coats unthinned.

FIBERGLASS: Sand thoroughly to remove gloss. Wash surface with SEARS EPOXY and LACQUER THINNER to remove grease, wax and mold release agent. Apply two or three finish coats unthinned.

METALS: Steel and Aluminum. Preparation of metal below the water line is extremely critical. Complete insulation from water is necessary to prevent pitting and other permanent damage. Remove rust and corrosion with steel wool or by sanding until the metal is bright. Sand pit marks smooth. Finish sand with very fine emery cloth to remove protruding metal shavings. Wash surface with SEARS EPOXY and LACQUER THINNER to remove traces of oil, grease or wax. Prime with SEARS MARINE METAL PRIMER following the instructions given on the label of that product. Apply two or three finish coats unthinned.

APPLICATION
For boats used in fresh water, apply a minimum of two coats of SEARS ANTI-FOULING BOTTOM PAINT. At least three coats should be used on boats used in salt water. For best results, avoid painting in direct sunlight. Stir paint thoroughly before and during application. Flow on paint generously with good quality natural bristle brush or enamel roller. Allow at least four hours drying time between coats. Allow at least forty-eight hours after application of last coat before boat is launched. Clean brushes and other tools with SEARS EPOXY and LACQUER THINNER immediately after using.

NOTE: Scratches and gouges that penetrate the paint to bare metal should be repaired to avoid damage from corrosion. Sand and clean sand damaged areas to bare metal and finish above with paint in painting metals.

COVERAGE: Approximately 100 sq. ft. of surface per quart.
Sold by SEARS, ROEBUCK AND CO. Chicago, IL 60644

KEEP OUT OF THE REACH OF CHILDREN.
DANGER
See for Additional Precautionary Statements

30 63614 RED
32 FL. OZ. (1 QT.)