

DO NOT SPRAY!

WEAR MASK WHILE SANDING TO AVOID BREATHING PAINT DUST. THE SPECIAL WATER RESISTANT ACRYLIC RESINS IN COMBINATION WITH TBTF PROVIDE EFFECTIVE PROTECTION AGAINST BARNACLES, TEREDOS, ALGAE, AND OTHER MARINE FOULING ORGANISMS.

RECOMMENDED FOR: All wood, plywood, fiberglass and properly primed metal boats.

FEATURES:

- TBTF (Tributyltin Fluoride) has been proven a most effective anti-fouling toxicant.
- The water-resistant acrylic base develops a hard, flat finish, yet allows proper release of TBTF to retard most growth or attachment.
- Formulated in "fade resistant" rich, bright colors.
- TBTF remains effective even if boat is pulled from water and relaunched frequently.

DIRECTIONS

BEFORE YOU PAINT:

Surface should be clean and sound. Check adhesion of old paint with a knife blade before painting over previously painted surfaces. If old paint lifts easily or is in generally poor condition it should be removed. Previous coats of "soft" or "semi-hard" bottom paints, identifiable by a chalky or powdery feel, should be completely removed. Use Sears PAINT and VARNISH REMOVER (except on fiberglass) or power sanding to remove old paint.

OLD PAINT IN GOOD CONDITION:

Sand thoroughly to remove gloss, then wipe with Sears EPOXY and LACQUER THINNER. Apply two or three finish coats unthinned.

NEW OR UNFINISHED WOOD:

Sand thoroughly, fill seams and cracks. Apply first coat thinned 50% with Sears EPOXY and LACQUER THINNER and allow to dry several hours. Sand lightly before applying two or three finish coats unthinned.

FIBERGLASS:

Sand thoroughly to remove gloss. Wash surface with Sears EPOXY and LACQUER THINNER to remove grease, wax and old release agent. Apply two or three finish coats unthinned.

METALS (Steel and Aluminum)

Preparation of metal below the water line is extremely critical. Complete insulation from water is necessary to prevent pitting and other permanent damage. Remove all rust and corrosion with steel wool or by sanding until the metal is bright. Sand pitting marks on both. Finish sand with fine emery cloth to remove protruding metal shavings. Wash surface with Sears EPOXY and LACQUER THINNER or SAND-BLAST to remove traces of oil, grease or wax. Prime with Sears MARINE METAL PRIMER following the instructions given on the label for that product. Apply two or three finish coats unthinned.

APPLICATION:

For boats used in fresh water, apply a minimum of two coats of Sears ANTI FOULING BOTTOM PAINT. At least three coats should be used on boats used in salt water.

For best results, avoid painting in direct sunlight. Stir paint thoroughly before and during application. Flow on paint generously with good quality natural bristle brush or enamel roller. Allow at least four hours drying time between coats. Allow at least forty eight hours after application of last coat before boat is launched. Clean brushes and other tools with Sears EPOXY and LACQUER THINNER immediately after using.

NOTE: Scratches and gouges that penetrate the paint to bare metal should be repaired to avoid damage from corrosion or "galvanic action." Sand damaged areas to bare metal and follow above directions for painting metals.

COVERAGE: Approximately 100 sq. ft. (9.3 sq. meters) per quart

Sold by SEARS, ROEBUCK AND CO., Chicago, IL 60684



DIRECTIONS FOR USE

It is important to agitate thoroughly when mixing with water and continue agitation while spraying.

This product is for use as a general purpose herbicide. Avoid contact with desirable plants which you wish to destroy. Spray thoroughly and continue agitation while spraying.

GENERAL WEED CONTROL

Apply this product to the weeds in the field. Spray thoroughly and continue agitation while spraying. Do not use on food or feed crops.

PCP — 10

EMULSIFIABLE CONCENTRATE

ACTIVE INGREDIENTS:

Pentachlorophenol
Other chlorophenols and related compounds
Aromatic Petroleum Derivative Solvent

INERT INGREDIENTS

TOTAL

Each gallon of this concentrate contains 10 pounds of active ingredients.

KEEP OUT OF REACH OF CHILDREN CAUTION

Harmful if swallowed or absorbed through skin! Causes skin irritation. Do not breathe vapor, fumes or spray mist. Do not get on skin, or on clothing. Wash thoroughly after handling or spraying.

Avoid spraying on plants which are not to be destroyed.
Do not use on food or feed crops.

APPLY THIS PRODUCT ONLY AS SPECIFIED ON LABEL.

U.S. STANDARD MEASURE — GALLONS

Sears

MARINE



ANTI-FOULING BOTTOM PAINT



with TBTF for salt or fresh water

DANGER

May cause severe eye burns. May cause eye damage. May be fatal if swallowed. May cause skin irritation or delayed chemical burns. Do not get in eyes, on skin, or on clothing. Very harmful. Avoid breathing of fumes or sanding dust. Wear goggles or face shield and rubber gloves while painting.

COMBUSTIBLE. DO NOT USE. POUR, SPILL, OR STORE NEAR HEAT OR OPEN FLAME.

Use with adequate ventilation. Close room when painting. Do not re-enter until fumes have cleared. It by inhaling fumes. If in eyes, flush with plenty of water. If on skin, wash with plenty of soap and water. Wash contaminated clothing before re-use. If swallowed CALL PHYSICIAN IMMEDIATELY.

AVOID CONTACT WITH SKIN. If in eyes, flush with plenty of water for at least 15 minutes and get medical attention. Wash skin with plenty of soap and water. Wash contaminated clothing before re-use. If swallowed CALL PHYSICIAN IMMEDIATELY.

DANGER

DO NOT REACH FOR