

MARINE

EPA EST. NO. 8788-TX-1

with TBTF for salt or fresh water

In case of contact, immediately flush eyes with plenty of water for at least 15 minutes, and get medical attention. Wash skin with plenty of soap and water. Wash contaminated clothing before reuse. Use if swallowed after R-11. CAN IMMEDIATELY.

* Active Ingredient (Tributyltin fluoride)	17.9%
Inert Ingredients	82.1%
	100.0%
Metallic Tin	7.27%

000-1-1987

539-277

**DO WE
TAN
BAF
REC
FEA**

■
■
■
■

**BEI
Sur
ove
be
pow
fibe**

DAPI
For
At
For
Flu
hou
boa
me
NO
dan
dire
CO

SEARS MARINE

FORMULA • 6363 B
GREEN

PIGMENT 17 1/2	
Titanium Dioxide	32.0
Type III	9.7
Zinc Oxide	2.4
Yellow Iron Oxide	2.4
Carbon Phthalocyanine	
Green	1.8
VEHICLE 82 2	
Acrylic Polyester Resin	17.5
Xlenes Mon. Boiling	30.4
Ethyl Gly. of Acetate	15.5
Tributyltin Fluoride	19.5

Tint to color less than 5%

EPA REG. NO. 539-278AA

EPA EST. NO. 8788-TX-1



ANTI-FOULING BOTTOM PAINT



with TBTF for salt or fresh water

ANGER

May cause severe eye burns. May cause eye damage. May be fatal if swallowed. May cause skin irritation or delayed chemical burns. Do not get in eyes, on skin, or on clothing. Wash thoroughly with soap and water. If swallowed, call physician. Wear goggles, gloves, and other protective clothing.

COMBUSTIBLE. DO NOT USE NEAR OPEN FLAME.

Use with adequate ventilation. Use with adequate ventilation. Do not reuse empty container. Destroy by perforating or crushing. Bury or discard in a safe place. Do not contaminate water by leakage of equipment or disposal of wastes.

ANTIDOTE STATEMENT

In case of contact, immediately flush eyes with plenty of water for at least 15 minutes, and get medical attention. Wash skin with plenty of soap and water. Wash container thoroughly before reuse. If swallowed, call physician immediately.

DO NOT SPRAY!

WEAR MASK WHILE SANDING TO AVOID BREATHING PAINT DUST. THE SPECIAL WATER RESISTANT ACRYLIC RESINS IN COMBINATION WITH TBTF PROVIDE EFFECTIVE PROTECTION AGAINST BARNACLES, TEREDOS, ALGAE, AND OTHER MARINE FOULING ORGANISMS.

RECOMMENDED FOR: All wood, plywood, fiberglass and properly primed metal boats.

FEATURES:

- TBTF (Tributyltin Fluoride) has been proven a most effective anti-fouling toxicant.
- The water-resistant acrylic base develops a hard, flat finish, yet allows proper release of TBTF to retard most growth or attachment.
- Formulated in "fade-resistant" rich, bright colors.
- TBTF remains effective even if boat is pulled from water and re-launched frequently.

DIRECTIONS

BEFORE YOU PAINT:

Surface should be clean and sound. Check adhesion of old paint with a knife blade before painting over previously painted surfaces. If old paint lifts easily or is in generally poor condition it should be removed. Previous coats of "soft" or "semi-hard" bottom paints, identifiable by a chalky or powdery feel, should be completely removed. Use SEARS PAINT and VARNISH REMOVER (except on fiberglass) or power sanding to remove old paint.

OLD PAINT IN GOOD CONDITION:

Sand thoroughly to remove gloss, then wipe with SEARS EPOXY and LACQUER THINNER or SAND BAN. Apply two or three finish coats uniformly.

NEW OR UNFINISHED WOOD:

Sand thoroughly to remove saw marks and cracks. Apply first coat thinned 25% with SEARS EPOXY and LACQUER THINNER. Allow to dry seven hours. Sand lightly before applying two or three finish coats uniformly.

FIBERGLASS:

Sand thoroughly to remove gloss. Wash surface with SEARS EPOXY and LACQUER THINNER to remove grease, wax and mold release agent. Apply two or three finish coats uniformly.

METALS (Steel and Aluminum)

Preparation of metal below the water line is extremely critical. Complete insulation from water is necessary to prevent pitting and other permanent damage. Remove all rust and corrosion with steel wool or by sanding until the metal is bright. Sand pit marks smooth. Finish coat with two, three, or four coats of SEARS ANTI-FOULING BOTTOM PAINT. Wash surface with SEARS EPOXY and LACQUER THINNER or SAND BAN to remove traces of oil, grease or wax. Prime with SEARS MARINE METAL PRIMER following the instructions given on the label of that product. Apply two or three finish coats uniformly.

APPLICATION:

For boats used in fresh water, apply a maximum of two coats of SEARS ANTI-FOULING BOTTOM PAINT. At least three coats should be used on boats used in salt water. For best results, avoid painting in direct sunlight. Stir paint thoroughly before and during application. Flow on paint generously with medium stiff brush, roller, or spray gun. Allow at least four hours drying time between coats. Allow at least forty-eight hours after application of last coat before boat is launched. Clean brushes and other tools with SEARS EPOXY and LACQUER THINNER immediately after using.

NOTE: Scratches and gouges that penetrate the paint to bare metal should be repaired to avoid damage from corrosion or "galvanic action." Sand damaged areas to bare metal and follow above directions for painting metals.

COVERAGE: Approximately 100 sq. ft. (9.3 sq. meters) per quart.

Sold by SEARS, ROEBUCK AND CO., Chicago, IL 60684

30 63634 GREEN
32 FL.OZ. (1 QT.)
(95 LITERS)

DANGER!
KEEP OUT OF REACH OF CHILDREN
See side for other precautions.

*Active Ingredient
(Tributyltin Fluoride) 18.5%
Inert Ingredients 81.5%
100.0%
Metallic Tin 7.50%

ACCEPTED

OCT 1 1975

Use
For
EPA Reg. No. 539-278AA