



CENTER PANEL

KATHON 893 TP 25%

Industrial Fungicide for Use in
Coatings, Caulks and Sealants,
Wallpaper Adhesives, Aqueous Emulsions
and Adhesives, Polymer Compounds
and Fabrics

ACTIVE INGREDIENT:

| | |
|--|-------------|
| 2-n-octyl-4-isothiazolin-3-one | 25% |
| INERT INGREDIENTS: | 75% |
| TOTAL | 100% |

**KEEP OUT OF REACH OF CHILDREN
DANGER**

STATEMENT OF PRACTICAL TREATMENT

In case of contact, immediately flush eyes with plenty of water for at least 15 minutes and call a physician. Wash skin with soap and plenty of water. Remove and wash contaminated clothing before re-use.

If inhaled, remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen. Call a physician.

If swallowed, dilute by giving water to drink and call a physician. Never give anything by mouth to an unconscious person.

NOTE TO PHYSICIAN:

Probable mucosal damage may contraindicate the use of gastric lavage. Measures against circulatory shock, respiratory depression, and convulsions may be needed.

MANUFACTURED BY:
ROHM AND HAAS COMPANY
PHILADELPHIA, PA 19105

EPA Est. No. 707-PA-1
EPA Reg. No. 707-

Net Contents _____
Gallons

RIGHT PANEL

FABRICS

For use as a mildewcide on fabrics.

To protect fabric from mildew for up to four weeks, use 0.3 fluid ounces of Kathon 893 TP 25% fungicide in the final rinse for every 100 pounds of treated fabric.

Longer term protection may be obtained by padding between 0.075 and 0.125 pounds of Kathon 893 TP 25% in an aqueous or solvent dispersion onto 100 pounds of fabric.

Kathon 893 TP 25% weighs 8.6 lbs./gallon.

STORAGE AND DISPOSAL

PROHIBITIONS:

This product is corrosive to mild steel. Do not store or transport in unlined metal containers. Do not contaminate with strong oxidizing or reducing agents. Do not contaminate water, food, or feed by storage or disposal or cleaning of equipment.

PESTICIDE DISPOSAL:

Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional office for guidance.

CONTAINER DISPOSAL

METAL CONTAINERS:

Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

PLASTIC CONTAINERS:

Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by incineration, or, if allowed by state and local authorities, by burning. If burned, stay out of smoke.

GENERAL:

CONSULT FEDERAL, STATE, OR LOCAL DISPOSAL AUTHORITIES FOR APPROVED ALTERNATIVE PROCEDURES.

RIGHT PANELDIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

COATINGS

For use as a mildewcide in coatings such as latex paints and solvent based paints. Use 1.8 to 7.2 pounds of Kathon 893 TP 25% fungicide per 100 gallons of coating formulation. To insure uniform distribution throughout the formulation it is recommended that Kathon 893 TP 25% be preblended along with the coatings vehicle in the letdown phase before the final formulation step.

CAULKS AND SEALANTS

For use as a mildewcide in caulks and sealants. Use 6.5 to 9.0 pounds of Kathon 893 TP 25% fungicide per 100 gallons of caulk or sealant formulation. To insure uniform distribution throughout the formulation it is recommended that Kathon 893 TP 25% be preblended along with other ingredients such as solvents, plasticizers, or freeze-thaw stabilizers before the final formulation step.

WALLPAPER ADHESIVES

For use as a mildewcide to protect wallpaper pastes from fungal attack after they are applied. Use 0.13 to 0.18 pounds of Kathon 893 TP 25% fungicide per 100 pounds of wallpaper adhesive formulation. To insure uniform distribution throughout the formulation it is recommended that Kathon 893 TP 25% be preblended with water or other liquid components before the final formulation step.

AQUEOUS EMULSIONS AND ADHESIVES

For use as a mildewcidal preservative in water-based emulsions and adhesives. Use 0.05 pounds of Kathon 893 TP 25% fungicide in 100 pounds of emulsion or adhesive formulation. To insure uniform distribution throughout the formulation it is recommended that Kathon 893 TP 25% be preblended with water or other liquid components before the final formulation step.

POLYMER COMPOUNDS

For use as a mildewcide in PVC, polyurethane, and other polymer compounds. Use 0.16 to 0.40 pounds of Kathon 893 TP 25% fungicide in 100 pounds of compounded polymer system. To insure uniform distribution throughout the formulation it is recommended that Kathon 893 TP 25% be preblended with plasticizer or other liquid ingredients before the final compounding step.