



PENTA PLUS 40

WOOD PRESERVATIVE

1022-120

DIRECTIONS

To make a 5% ready-to-use solution, mix one part of this concentrate with ten parts by volume of a suitable petroleum solvent such as mineral spirits or kerosene.

As Penta Plus 40 is a concentrate, do not use without diluting.

WOOD PRESERVATION

After diluting as indicated above the ready-to-use Penta Plus 40 solution can be applied to lumber, poles, post and other wood products by a hot-cold bath process, by soaking, spraying, or brushing. The most effective treatment is obtained where deep penetration and high absorptions result. Soaking or a hot-cold bath process gives better results than does spraying or brushing and should be used where possible. Fence posts should be barked and air seasoned until dry and then soaked 34 to 48 hours. The butts should be well treated. Lumber for steps, sills, etc. should be soaked for at least 12 hours. When the wood is not in ground contact, brushing or swabbing may be used. The joints should be thoroughly drenched.

INGREDIENT STATEMENT

ACTIVE INGREDIENTS:

- Pentachlorophenol..... 35.3%*
- Other chlorinated phenols..... 4.1%*
- Petroleum solvent..... 59.0%

INERT INGREDIENTS..... 1.6%

*Equivalent to 41% pentachlorophenol, technical, as defined by Federal Spec. TT-W-570

WARNING

KEEP OUT OF REACH OF CHILDREN!

Harmful if swallowed or absorbed through skin! Causes skin irritation. Do not breathe vapor or spray mist. Do not get in eyes, on skin or on clothing. Wash thoroughly after handling. Wear rubber gloves and protective clothing when handling freshly-treated lumber.

Do not reuse empty drum. Return to drum reconditioner or destroy by perforating or crushing and burying in a safe place.

This product is toxic to fish and wildlife. Keep out of lakes, streams or ponds. Do not contaminate water by cleaning of equipment or disposal of wastes. DO NOT USE, POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME.

The solution obtained by diluting this concentrate with ten volumes of petroleum solution is a proven wood preservative and is especially recommended for the use of termite exterminators and others wishing to protect buildings from the ravages of these insects. Wood treated with ready-to-use solution is not paintable. If it is desired to paint treated wood, Penta WR should be used.

This concentrated pentachlorophenol solution complies with all requirements of Commercial Standard CS 19453, as developed by the trade under the procedure of the commodity Standards Division and issued by the U.S. Department of Commerce.

NON-WARRANTY

Neither the manufacturer nor the seller makes any representation or warranty, expressed or implied, concerning this material, except that it is of standard quality. Neither shall be held responsible in any manner for any personal injury, property damage or other type of loss resulting from the handling, storage or use of this material. Buyer assumes all risk of use and/or handling of this material when such use and/or handling is contrary to label instructions.

5/8/1972

Paper 132

0000000000

4272

ACCEPTED
MAY 08 1972
UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND RODENTICIDE ACT
FOR ECONOMIC POISON REGISTERED
UNDER NO. 0000000000 SUBJECT
TO ATTACHED COMMENTS

232