



# Penta-WR *Ready-to-Use* WOOD PRESERVATIVE

NET CONTENTS \_\_\_\_\_ GALLONS

**WATER REPELLENT—CLEAR—PAINTABLE  
STOPS ROT—KILLS TERMITES  
CONTROLS WARPING—SWELLING**

1022-356  
**ACCEPTED**  
OCT 24 1972  
FEDERAL BUREAU OF INVESTIGATION  
FOR THE DEPARTMENT OF JUSTICE  
ED UNDER NO. 100-100000-100000  
SUBJECT TO ATTACHED COMMENTS

READ THIS LABEL BEFORE USING PRODUCT

## RECOMMENDED USE

Windows, window frames, doors, stairs, porches, shingles, trellises, steps, subflooring, interior trim, wall paneling, furniture, fence pickets, fence rails, furring strips, arbors, flooring and beverage cases. Powderpost beetles which invade furniture, flooring, and structural lumber are killed by application of this preservative. These insects will not attack the treated wood.

In addition to preventing decay, blue stain, and insect attack on wood this preservative controls warping, swelling, shrinking, and end checking caused by changes in moisture content of lumber and plywood products.

Wood to be protected against subterranean termites should be treated before use in construction. Termites will not attack wood treated with PENTA WR.

This product is toxic to fish and wildlife. Keep out of lakes, streams or ponds. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

### ACTIVE INGREDIENTS:

Pentachlorophenol.....	4.47%
Other chlorinated phenols.....	0.52%
Petroleum hydrocarbons.....	88.03%
<b>INERT INGREDIENTS:</b> .....	6.98%
Total.....	100.00%

\*Equivalent to 5.2% Technical Pentachlorophenol as defined by Fed. Spec. TT-W-570.

## WARNING

### KEEP OUT OF THE REACH OF CHILDREN!

Harmful or fatal if swallowed or absorbed through skin. Causes skin irritation. Do not breathe vapor or spray mist. Do not get in eyes, on skin or on clothing. Wash thoroughly after handling.

Do not use, pour, spill or store near heat or open flame.

Do not reuse empty container. Destroy it by burying with waste or burning. Stay away from smoke or fumes.

## DIRECTIONS

The best results will be obtained if wood to be treated is immersed for 3 minutes or longer. If dipping is not possible, 2 liberal brush or spray applications should be applied. Allow at least 1 hour between applications. Make certain all areas are fully treated to get the maximum benefits. Allow 24 hours or longer after application of the preservative prior to painting. Less paint is needed over wood treated with this water repellent wood preservative.

Fence posts, poles, foundation timbers and heavy wooden members should be free of bark, dry and well-seasoned and immersed in the product (dilute product) for a period of 12 to 48 hours to be an effective wood preserver.

In areas where dry wood termites are present all interior trim as well as millwork should be given a 3-minute dip.

Wear protective clothing and rubber gloves when handling the freshly treated lumber.

Neither the manufacturer nor the seller makes any representation or warranty, expressed or implied concerning this product, except that it is of the manufacturer's standard quality. Neither shall be held responsible in any manner for any personal injury, property damage or other type of loss resulting from the improper handling, storage and use of this product. The buyer accepts and uses this product on these conditions.

EPA REG. NO. 1022-356

MANUFACTURED BY **CHAPMAN CHEMICAL COMPANY** MEMPHIS, TENNESSEE