



NET \_\_\_\_\_ LBS.

# POL-NU<sup>®</sup> TYPE WOOD PRESERVATIVE GREASE

CONTAINING SODIUM TETRABORATE (BORAX)

READ THIS LABEL BEFORE USING PRODUCT

## ROUND THE TREATMENT

OF STUMP AND PILE IN THE PROTECTION AGAINST TERMITES  
Towards Service Life of Standing Piles and Posts.

### INGREDIENTS

ACTIVE INGREDIENTS	
Pentachlorophenol	8.95
Fiber cellulosic solids	1.04
Sodium tetraborate dihydrate	15.50
Aromatic solvent	67.74
INERT INGREDIENTS	6.77
<b>Total</b>	<b>102.00</b>

Net weight 102.00 lbs. of pentachlorophenol as analyzed by  
method 1631 of EPA 821-70a.

**ACCERTED**  
Apr 7, 1970  
UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC PESTICIDE REGISTRATION  
NO. UNDER NO. 1022-368

### WARNING

AVOID CONTACT WITH EACH OF CHEMICALS  
which are absorbed through the skin. Do not get  
clothing or hands wet. Wash hands with plenty of soap and water.  
Keep away from food, feed, children, pets and livestock. If  
taken internally, induce vomiting and CALL A PHYSICIAN AT ONCE.

USDA Reg. No. 1022-368

### APPLICATION TO POLES

TIMPREG B can best be applied to poles by using with the CHAPMAN  
BANDAGE MAKER and polyethylene coated kraft paper. TIMPREG B  
may also be applied by brush, paddle, shovel, or by mechanically  
driven pump. For application to deep checks in poles or stumps, fill  
a caulking gun with TIMPREG B and apply. Any special equipment  
that will handle No. 2 grease will work with TIMPREG B.

Excavate the soil away from the poles to a depth of about 18 inches  
in areas of medium to heavy rainfall and 24 inches or deeper in areas  
of low rainfall. Use brush the pole surface to remove standing soil.  
Scrape off any decay on the surface. It is also desirable to take an  
excavation from the center of the pole or stump with  
a hand-dug hole to the center of the pole or stump.

Fill the hole with TIMPREG B grease by using the CHAPMAN  
BANDAGE MAKER.

Apply TIMPREG B grease to the ground around the pole or stump.  
The hole should be filled with TIMPREG B grease to a depth of  
18 inches or deeper in areas of low rainfall. The hole should be  
filled with TIMPREG B grease to a depth of 24 inches or deeper in  
areas of medium to heavy rainfall. A hole 3 inches in diameter  
should be dug around the pole or stump and 3 inches above the  
ground.

More than one hole may be used in some cases where the pole  
or stump diameter is greater than 12 inches. The hole should be  
filled with TIMPREG B grease to a depth of 24 inches or deeper in  
areas of medium to heavy rainfall. A hole 3 inches in diameter  
should be dug around the pole or stump and 3 inches above the  
ground to obtain an 18 inch band.

### NON-WARRANTY

Neither the Manufacturer nor the seller makes any representation or warranty, expressed or implied concerning this product, except that it is of the Manufacturer's standard quality. Neither shall be held responsible in any manner for any personal injury, property damage or other type of loss resulting from the improper handling, storage and use of this product. The buyer accepts and uses this product on these conditions.

MANUFACTURED BY **CHAPMAN CHEMICAL COMPANY** MEMPHIS, TENNESSEE