



POL-NU 15-15

U.S. Patent No. 2,904,467

MAR 25 1981

Approved by the Federal Insecticide, Fungicide, and Rodenticide Administration, U.S. Department of Agriculture, for use as a wood preservative. Registered under EPA Reg. No. 1022-404

PENTA PRESERVATIVE GREASE WITH CREOSOTE ADDED GROUNDLINE TREATMENT

FOR CONTROL OF DECAY AND AIDS IN THE PROTECTION AGAINST TERMITES
Extends Service Life of Standing Poles and Posts.

WARNING

Harmful or fatal if swallowed or absorbed through skin. Do not breathe fumes. Do not get on skin or clothing. Wear rubber gloves when handling lumber wet with solution. Causes eye damage. Wear goggles or face shield when handling. In case of skin contact wash with soap and water; for eyes, flush with water for at least fifteen minutes and get medical attention. In case of swallowing, induce vomiting by giving an emetic such as a teaspoon of mustard in water followed by flour and water. CALL A PHYSICIAN IMMEDIATELY.

Keep away from animals. Avoid contact with feed and foodstuffs. Keep out of potable water supplies. Do not reuse empty drum. Return to drum reconditioner or destroy by perforating or crushing and burying in a safe place.

EPA Reg. No. 1022-408
EPA Est. No. 1022-TN-1

INGREDIENTS

ACTIVE INGREDIENTS:	
Pentachlorophenol	12.9%
Other Chlorinated Phenols	1.5%
Creosote	15.5%
Aromatic Petroleum Derivative Solvent	60.5%
INERT INGREDIENTS:	
TOTAL	100.0%

CAUTION

KEEP OUT OF REACH OF CHILDREN

This product is toxic to fish and wildlife. Keep out of lakes, streams, or ponds. Do not contaminate water by cleaning of equipment, or disposal of wastes. Apply this product only as specified on this label.

APPLICATION TO POLES

POL-NU 15-15 can best be applied to poles by using the CHAPMAN POL-NU BANDAGE MAKER and POL-NU paper. For application to deep checks in poles or timber, fill a caulking gun with POL-NU 15-15 and apply. Any grease equipment that will handle No. 2 cup grease will work with POL-NU 15-15. Excavate the soil away from the poles to a depth of about 18 inches. Wire brush the pole surface to remove adhering soil. Scrape off any decay on the surface. It is also desirable to take increment borings directed toward the center of the pole. Holes should be plugged with locust plugs or treated wood plugs. If decay is present in the center of the pole, consideration should be given to its early replacement or stubbing. POL-NU 15-15 will penetrate wet wood. It is not necessary to leave excavated poles exposed in order to dry out. POL-NU 15-15 should be applied in a 1/4 inch thickness. More may be required for special conditions. (CHAPMAN POL-NU BANDAGE MAKER is adjustable up to 3/8 of an inch. Bandages may be prepared to cover ground-line areas of poles in bands 18 to 22 inches in height. (The POL-NU BANDAGE MAKER produces a 22 inch band of grease. A template furnished separately may be inserted to obtain an 18 inch band. POL-NU 15-15 should be applied to cover the pole surface 4 inches below the last evidence of decay and 3 inches above the ground-line. More than one bandage may be used in special cases where the pole area to be covered spans a height greater than 22 inches, such as on hillsides, etc.

NOTICE

Neither Chapman Chemical Company nor the seller makes any representation or warranty, expressed or implied, concerning this material, other than indicated on the label. Neither shall be held responsible in any manner for any personal injury or property damage or other type of loss resulting from the improper handling, storage or use of this material. The buyer accepts and uses this material on these conditions

CHAPMAN CHEMICAL COMPANY

MEMPHIS, TENNESSEE 38109