



COPPER NAPHTHENATE WR

WOOD PRESERVATIVE

AC

Oct 9, 1961

1027-101

Ready-to-Use

MEETS FEDERAL SPECIFICATION TT-W-572
TYPE II, COMPOSITION B

DIRECTIONS FOR USE

The best results will be obtained if wood to be treated is immersed for 3 minutes or longer. If dipping is not possible, 2 literal brush or spray applications should be applied. Allow at least 1 hour between applications. Make certain all areas are fully treated to get the maximum benefits. Allow 24 hours or longer after application of the preservative prior to painting.

In addition to preventing decay, blue stain, and insect attack on wood this preservative controls warping, swelling, shrinking, and end-checking caused by changes in moisture content of lumber and plywood products.

Wood to be protected against subterranean termites should be treated before use in construction. Termites will not attack wood treated with Copper Naphthenate WR Wood Preservative.

INGREDIENT STATEMENT

ACTIVE INGREDIENTS:

| | |
|-------------------------------|--------|
| Copper Naphthenate | 2.00% |
| Aromatic Petroleum Derivative | 68.25% |

INERT INGREDIENTS:

| | |
|-------|---------|
| | 29.75% |
| Total | 100.00% |

Copper Naphthenate meets AWWA Specification P8.

WATER REPELLENT
STOPS ROT — PREVENTS
CONTROLS WARPING — SWELLING

CAUTION

KEEP OUT OF REACH OF CHILDREN

(See label for other caution statements)

CAUTION

Harmful if swallowed.
Do not breathe vapor or spray mist.
Do not get in eyes, on skin or on clothing.
Wash thoroughly after handling.

RECOMMENDED USE

Windows, window frames, doors, stairs, porches, shingles, trellises, steps, subflooring, interior trim, wall paneling, furniture, fence posts, fence rails, furring strips, arbors, flooring and beverage cases. Powder-post beetles which invade furniture, flooring, and structural lumber are killed by application of this preservative. These insects will not attack the treated wood.

NOTICE

Neither the Manufacturer nor the seller makes any representation or warranty, expressed or implied concerning this product, except that it is of the Manufacturer's standard quality. Neither shall be held responsible in any manner for any personal injury, property damage or other type of loss resulting from the improper handling, storage and use of this product. The buyer accepts and uses this product on these conditions.