

NET CONTENTS

GALLONS



Q-SAN Ready-to-Use

WATER REPELLENT WOOD PRESERVATIVE

Controls ROT, STAIN, MOLD. Retards WATER ABSORPTION, SWELLING.

ACCEPTED

Especially for use on wood to be used on or near fruits and vegetables.

AUG 29 1974
UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND RODENTICIDE ACT
FOR ECONOMIC POISON REGISTERED
ED UNDER NO. 1022-485 SUBJECT
TO ATTACHED COMMENTS.

DIRECTIONS

Q-San Ready-to-Use Solution requires no dilution before use. Use as received, following label directions.

TREATMENT OF RE-USABLE CONTAINERS SUCH AS FIELD PICKING BOXES

Immerse the boxes for 30 seconds if they are made of species such as sap gum, poplar, cottonwood, pine. Drain thoroughly, stack, and allow solvent to evaporate before use. This will require about 48 hours* when the weather is warm and dry. During cold or rainy weather it is best to allow a longer drying period. Boxes should preferably be dipped when new. If old boxes are dipped, make sure they are free of debris that would retard penetration of the solution.

EPA REG. NO. 1022-485

INGREDIENT STATEMENT

ACTIVE INGREDIENTS:
Copper 8-quinolinolate*.....0.27%
INERT INGREDIENTS:99.73%
Total.....100.00%

*Equivalent to 0.049% metallic copper.

CAUTION

KEEP OUT OF THE REACH OF CHILDREN!

Do not allow this solution to come in contact with eyes and remove from skin with synthetic detergent and water. Harmful if swallowed. Be sure all solvent evaporates from treated wood before using same or damage may be sustained by fruit or vegetable.

This product is toxic to fish. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

Do not reuse empty drum. Return drum to reconditioner or destroy by perforating or crushing and burying in a safe place away from water supplies.

DO NOT USE, POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME.

TREATMENT OF ONE TRIP CONTAINERS

Where mold prevention on containers such as bean or tomato hampers, bushel baskets and the like is desired, an instantaneous immersion is sufficient. The containers should then be drained and the solvent allowed to evaporate.

SEVERE EXPOSURE APPLICATIONS

For treatment of wood to be used in contact with soil, higher retentions are desirable and longer treating periods are usually necessary. Wood used in very damp places where condensation is likely to be heavy (such as inside refrigerators, in showers or wash rooms) also need longer treatment. For example, air dried southern yellow pine sapwood dimension and boards will require one to two hours of soaking. Kiln dried southern yellow pine sapwood boards require about 24 hours of soaking.

GREEN HOUSES AND GARDENING

Treat green house flats with Q-San Water Repellent Wood Preservative to prevent decay, mold, and stain. After the solvent evaporates no injury will result to the young plants. Tomato and bean stakes will last much longer if treated with Q-San Water Repellent Wood Preservative. Plants or fruit will not be harmed by the treated wood.

For treating follow directions listed under "Severe Exposure Application."

Other wood species should be soaked in Q-San Water Repellent Wood Preservative as follows: Ash, Hickory, Hackberry, Red Oak, Larch, White Pine, 48 hours, Elm, Black Gum, 24 hours.

NOTICE

Neither the Manufacturer nor the seller makes any representation or warranty, expressed or implied concerning this product, except that it is of the Manufacturer's standard quality. Neither shall be responsible in any manner for any personal injury, property damage or other type of loss resulting from the improper handling storage and use of this product. The buyer accepts and uses this product on these conditions.

*24 hours if VM and P naphtha is used as the diluent.

MANUFACTURED BY **CHAPMAN CHEMICAL COMPANY** MEMPHIS, TENNESSEE