



# Q-SAN CONCENTRATE 1 TO 10 WATER REPELLENT WOOD PRESERVATIVE

NET CONTENTS

GALLONS

## DIRECTIONS

To one part of Q-San Water Repellent Wood Preservative Concentrate, add 10 parts of mineral spirits, VM and P naphtha, Standard solvent or 9 parts xylol. Mineral spirits and Standard solvent evaporate treated wood more slowly, but are less costly than VM and P naphtha or xylol.

## TREATMENT OF RE-USABLE CONTAINERS SUCH AS FIELD PICKING BOXES

Immerse the boxes for 30 seconds if they are made of species such as sap gum, poplar, cedar, wood, pine. Drain thoroughly, stack, and allow solvent to evaporate before use. Old boxes will require about 48 hours\* when the weather is warm and dry. During cold or rainy weather it is best to allow a longer drying period. Boxes should preferably be dipped when new. If old boxes are dipped make sure they are free of debris that would retard penetration of the solution.

\*48 hours if VM and P naphtha is used as the diluent.

## TREATMENT OF ONE TRIP CONTAINERS

Where cold prevention in containers such as bean or tomato hampers, bushel baskets and the like is desired, an instantaneous immersion is sufficient. The containers should then be drained and the solvent allowed to evaporate.


Q-SAN 1-22-3-1

CONTROLS ROT, STAIN, MOLD. RETARDS WATER ABSORPTION, SWELLING. ESPECIALLY FOR USE ON WOOD TO BE USED ON OR NEAR FRUITS AND VEGETABLES.

## INGREDIENT STATEMENT

ACTIVE INGREDIENT:	
Copper 8-quinolinolate*.....	2.87%
INERT INGREDIENTS:.....	97.13%
TOTAL.....	100.00%

\*Equivalent to 0.5177 metallic copper



## CAUTION

KEEP OUT OF REACH OF CHILDREN!

Do not allow this solution to come in contact with eyes and remove from skin with synthetic detergent and water. Harmful if swallowed. Be sure all solvent evaporates from treated wood before using; same or damage may be sustained by fruit or vegetable.

This product is toxic to fish. Keep out of lakes, streams, or ponds. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

Do not reuse empty drum. Return drum to reconditioner or destroy by perforating or crushing and burying in a safe place away from water supplies.

DO NOT USE, POUR, SPILL, OR STORE NEAR HEAT OR OPEN FLAME.

MANUFACTURED BY CHAPMAN CHEMICAL COMPANY, CHICAGO, ILL.

## SEVERE EXPOSURE APPLICATIONS

For treatment of wood to be used in contact with soil, higher retentions are desirable and longer treating periods are usually necessary. Wood used in very damp places where condensation is likely to be heavy (such as inside refrigerators in showers or wash rooms) also need longer treatment. For example, air dried southern yellow pine sapwood dimension and boards will require one to two hours of soaking. Kiln dried southern yellow pine sapwood boards require about 24 hours of soaking.

## GREEN HOUSES & GARDENING

Treat green house flats with Q-San Water Repellent Wood Preservative to prevent decay, mold, and stain. After the solvent evaporates, no injury will result to the young plants. Tomatoes and bean stakes will last much longer if treated with Q-San Water Repellent Wood Preservative. Plants or fruit will not be harmed by the treated wood.

For treating follow directions listed under "Severe Exposure Application."

Other wood species that can be treated with Q-San Water Repellent Wood Preservative are: Fir, Spruce, Blueberry, Hackberry, Red Oak, Birch, White Pine, Elm, Black Gum, 24 hours.

## NOTICE

Neither the Manufacturer nor the seller makes any representation or warranty, expressed or implied, concerning this product, except that it is of the Manufacturer's standard quality. Neither is the Manufacturer responsible in any manner for any loss or damage, property damage or other injury or expense resulting from the improper use of this product.