



ACCEPTED

4 APR 1975

BUSAN® 30-I

UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND RODENTICIDE ACT
FOR ECONOMIC POISON REGISTRATION
ED UNDER NO. 1448-55

Patents issued or pending in the U.S.A. and other countries

Active ingredient:

2-(Thiocyanomethylthio)benzothiazole 30 percent

Inert ingredients 70 percent

APPLICATIONS

Busan 30-I is an emulsifiable liquid concentrate used to control sap stain and mold on freshly cut softwood and hardwood lumber, logs, poles, posts, and timbers. Busan 30-I is also used to inhibit the growth of fungi that cause the degradation of wood chips.

Lumber: Freshly cut lumber 2 inches or less in thickness should be dipped or sprayed until complete surface wetting is accomplished using a dispersion prepared by mixing 2.0 to 3.0 pounds (2 to 3 pints) of Busan 30-I in 100 U.S. gallons of water.

Logs: Spray the ends and barkless areas of the freshly cut logs with a dispersion of 4.0 to 6.0 pounds (4 to 6 pints) of Busan 30-I in 100 U.S. gallons of water.

Poles, Posts, and Timbers: Dip or spray until all surfaces are wetted in a dispersion of 4.0 to 6.0 pounds (4 to 6 pints) of Busan 30-I in 100 U.S. gallons of water.

Logs should be bright and free of infection when converted into lumber. For best protection during warm weather, lumber should be treated within 24 hours after being sawed. Busan 30-I should be thoroughly dispersed in water using a mixing tank or container of known capacity prior to being added to the dipping vat. The dipping vat should be protected from rain to prevent dilution of dispersion.

Treated lumber should not be exposed to heavy rains immediately after treatment. Lumber piles should be as narrow as practical, properly elevated, well-spaced, and adequately roofed.

Wood Chips: Use Busan 30-I at the rate of 1.0 to 2.0 pounds per ton of oven-dry wood. Busan 30-I should be applied to the wood so that the product is uniformly distributed over all exposed surfaces of the chips. A suggested method of application is through a water shower or spray located in the pneumatic-conveyor system carrying the chips from the chipper to the storage pile.

WARNING**KEEP OUT OF REACH OF CHILDREN**

Causes eye damage and skin irritation. May be harmful if absorbed through the skin. Do not get in eyes, on skin, or on clothing. Wear goggles or face shield and rubber gloves when handling. Harmful if swallowed. Avoid contamination of food.

FIRST AID: After any skin exposure, wash promptly and thoroughly with an abrasive soap and cool water and finally with glycerin. In case of persistent irritation of the skin, obtain medical attention. Remove and wash contaminated clothing before reuse.

If the product gets into the eyes, flood eyes immediately and thoroughly with cool water for 15 to 30 minutes. See a physician if any irritation persists.

If the product is swallowed, call a physician immediately. Give patient doses of powdered charcoal immediately or all he can swallow of raw egg whites, milk, gruel, or flour and water. Then induce vomiting with salt, soap, or mustard in warm water.

This product is toxic to fish. Keep out of lakes, streams, or ponds. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

Do not reuse empty container. Return to drum reconditioner or destroy by perforating and crushing and burying in a safe place.

MANUFACTURED BY
BUCKMAN LABORATORIES, INC.
MEMPHIS, TENN. 38108, U.S.A.