

G-C

OPEN VAT TYPE

COPPER NAPHTHENATE WOOD PRESERVER

FOR USE BY WOOD PRESERVING OPERATORS USING OPEN VAT METHOD OF TREATING LUMBER AND POSTS.

Active Ingredients

Copper Naphthenate	5%
Copper Metallic 0.5%	
Petroleum Distillate	95%
	100%

DIRECTIONS

FOR PREVENTION OF DECAY AND PROTECTION AGAINST TERMITES

Lumber or posts to be treated should be seasoned, dry, and allowed to remain in solution for 24 to 48 hours. Allow to dry before painting. Generally the coats of paint will cover.

CAUTION - POISON - IN PAINT

KEEP FROM REACH OF CHILDREN - IN PAINT

Do not burn, melt or store near fire or flames. Harmful if taken internally. Avoid prolonged contact with skin. Avoid inhalation of mists.

GEORGIA-CAROLINA OIL COMPANY
Macon, Georgia

Net Contents _____ Gallons

EPA Reg. 1686-10

