



**MOBILE
PAINTS**

Active Ingredient

Copper Naphthenate 20.0%

Inert Ingredient 80.0%

Total 100.0%

Copper as Metal 2.0%

LOT NO. XXXX

COP-R-TOX

REGISTERED U.S. PATENT OFFICE

PENETRATING LIQUID COPPER

PROTECTS AGAINST

WOOD ROT : TERMITES : FUNGUS

FOR MARINE USE

CAUTION!

**HARMFUL OR FATAL IF SWALLOWED
KEEP OUT OF REACH OF CHILDREN**

See other cautions on back panel

**MOBILE PAINT MANUFACTURING COMPANY
MOBILE, ALABAMA 36601**

COP-R-TOX FOR PROTECTION OF WOOD

Cop-R-Tox soaks into wood pores giving long lasting protection against termites and rot-causing fungus, mildew and mold. Its lack of water solubility aids its waterproofing qualities. The formula of Cop-R-Tox was tested in the Tropics by U.S. Government Agencies and found to be highly effective.

COP-R-TOX FOR MARINE USE

CANVAS, WOOD, ROPES, NETS AND SEINES

Cop-R-Tox saturates the fiber protecting against rot, mildew and fungus. Its waterproofing qualities adds to its exceptional value in the preservation of these materials and to its long life and strength.

WOOD BOATS

Cop-R-Tox affords protection against decay-causing fungus and mold in interior and exterior locations. It has particular utility in bilges and on surfaces to be painted. Cop-R-Tox, when applied to bare wood which will be below the waterline, will give 30 to 60 days protection in the event that the anti-fouling exterior coat of paint is scraped off by contact with pilings or other surfaces.

DIRECTIONS

Cop-R-Tox is a 20% copper naphthenate solution and each gallon may be thinned with one gallon of mineral thinner to produce a 10% copper naphthenate solution. Cop-R-Tox may be applied by brushing freely, spraying or dipping in a tank. For lumber Cop-R-Tox penetrates best and is most effective when wood is unpainted, dry and clean. Cop-R-Tox may be painted over in 24 hours as it contains no creosote or tar products. A green cast may be noted in the first priming coat but this is not bleeding and should not show in subsequent topcoats of enamel. All wood in contact with the earth or secured to concrete slabs should receive two flowing coats by brushing or spraying or be dipped for at least five minutes. Other wood surfaces require only one coat. Cop-R-Tox should be applied at the rate of 300 square feet per gallon.

CAUTION!

HARMFUL IF SWALLOWED

KEEP OUT OF REACH OF CHILDREN

Combustible! Do not use, pour, spill or store near heat or open flame. Contains petroleum distillate. For eye contact flood with water. **CALL PHYSICIAN IMMEDIATELY.** Avoid contact with skin and breathing of vapors or spray mists. Do not transfer contents to bottles or other unlabeled containers. Close container after each use. Do not take internally. Do not reuse empty container. Return to drum re-conditioner or destroy by perforating or crushing and burying in a safe place away from water supply.

USE WITH ADEQUATE VENTILATION

EPA Reg. No. 1719-2
XXXXGM74-1

1719-2

2-14-1974



1/2

2/2

ACCEPTED
FEB 14 1974
UNDER THE FEDERAL INSECTICIDE
AND RODENTICIDE ACT
FOR ECONOMIC PESTS
REGISTERED UNDER NO. 114-2 (U.S.)
ATTACHED COMMENTS.

114-2
114-2