

# BLP MOBILE PAINTS

ACTIVE INGREDIENT:	
..... Oxide .....	28.9%
..... INGREDIENTS: .....	61.7%
	<hr/>
	100.0%



A FOUNTAIN

## V-I-P

COLD PLASTIC ANTI-FOULING 473-71

MOBILE PAINT MFG. CO., INC.

### WARNING!

KEEP OUT OF REACH OF CHILDREN  
VAPOR HARMFUL  
See Other Cautions on Back Panel

ONE GALLON



# Jack Tar

## Marine Finishes

ACCEPT

*March 21, 1974*

UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC POISON REGISTERED  
UNDER NO. 229-52 SUBJECT  
TO ATTACHED COMMENTS.

### V-I-P

### COLD PLASTIC ANTI-FOULING 473-71

### MOBILE PAINT MFG. CO., INC. MOBILE, ALABAMA

#### WARNING!

KEEP OUT OF REACH OF CHILDREN  
VAPOR HARMFUL  
See Other Cautions on Back Panel

### ONE GALLON

Th  
an  
an  
be  
of  
su  
by  
pe  
St  
ch  
me  
3  
fo  
dr  
tic  
of  
le

This paint is intended to protect steel, wood, and fiberglass boats from fouling by barnacles and similar marine life. Disperse thoroughly before each use by pouring most of the liquid off and working any settled pigment into a smooth paste using a stiff paddle. Continue by adding small portions of the liquid to the paste until paint is completely mixed.

**Steel:** Hull should be cleaned by scraping, chipping and mechanical wire brushing to remove all rust and scale. Prime by applying 3 coats of Anti-Corrosive Primer 409-68 following the directions on the can. When dry apply 2 coats of Jack Tar VIP Cold Plastic Anti-Fouling 473-71 allowing a minimum of 4 hours between coats. Allow to dry at least overnight before returning to water.

**Wood:** If old surface, scrape clean and hose off with high pressure water and stiff brush. Allow to dry completely. If new work or cleaned old surface, apply 2 coats Anti-Corrosive Primer 409-68 following directions on the can. When dry apply 2 coats of Jack Tar VIP Cold Plastic Anti-Fouling 473-71 allowing a minimum of 4 hours between coats and at least overnight before returning to water.

**Fiberglass:** SAND THOROUGHLY with medium-fine grit sandpaper. Wash sanded surface with a CLEAN cloth saturated with Methyl Isobutyl Ketone to remove all traces of "mold release compound". Apply one very thin coat of BLP Jack Tar Wash Primer 409-42 followed by 2 coats of Jack Tar VIP Cold Plastic Anti-Fouling 473-71.

**NOTE: DO NOT use Linseed Oil to thin. Use BLP Xylol 75-15 (TT-X-916) if necessary.**

**CAUTION! COMBUSTIBLE**  
Contains Xylol

Keep away from heat and open flame. Avoid prolonged contact with skin or eyes and breathing of vapor or spray mist. In case of contact with eyes, flood repeatedly with water. CALL PHYSICIAN IMMEDIATELY. Do not transfer contents to unlabeled containers. Close container after each use. Do not reuse empty container. Destroy it by perforating or crushing. Bury or discard in a safe place away from water supply.

Do not contaminate water by cleaning of equipment, or disposal of wastes.

DO NOT USE, POUR, SPILL, OR STORE NEAR HEAT OR OPEN FLAME.

Use with adequate ventilation.

EPA EST. 1719-AL-1

EPA REG. NO. 1719-12

ONE GALLON

XBX IIT

KEEP OUT OF REACH OF CHILDREN

REN