

U.S. STANDARD





5 GAL. NET

Active Ingredients Cuprous Oxide 55.4% Inert Ingredients 44.6% 100.0% Total

FO OF

 \bigcirc

. .

2

M 7.2

.....

3. × 1

6 . .

; ; ; , ; ;

10

n;

 \bigcirc

ar en en el

XOXTT MIL-P-15931A

les **FI-FOULING** ORMULA NO. 121

DANGER! HARMFUL OR FATAL IF SWALLOWED VAPOR HARMFUL

MOBILE PAINTS

EYE IRRITANT KEEP OUT OF REACH OF CHILDREN See back panel for additional cautions

ACCEPTES JAN 1, 1670 1. J. T. M. < CIMMENT

This paint is intended for use on steel ship bottoms used in salt water to prevent fouling from barnacles and similar marine life.

The surface to be painted should be sandblasted and then given a coat of Wash Primer Specification MIL-P-15328B. Allow to dry 2 hours them apply four 1.5 Mil coats of Vinyl Red Lead Primer MIL-P-15929B or Vinyl-Zinc Chromate Primer MIL-P-15930B. This should be followed by two 2.0 Mil coats of Vinyl Anti-Fouling Mil-P-15931A .

Allow minimum of 4 hours dry time between all coats except Wash Primer and 4 hours after final coat of anti-fouling before launching. During conditions of high humidity or low temperature this dry time should be increased to a minimum of 8 hours.

If thinning is necessary use Vinyl Thinner or Methyl Isobutyl Ketone.

CONTAINS XYLOL AND METHYL ISOBUTYL KETONE

Avoid contact with eyes and breathing of vapor or spray mist. In case of contact with eyes, rlood repeatedly with water. CALL PHYSICIAN IM-MEDIATELY. Avoid prolonged contact with skin. Keep away from heat, sparks, and open flame. Contact with flame or hot surfaces may produce toxic gases. Do not transfer contents to unlabeled containers. Close container after each use. Do Not Take Internally.

Use with adequate ventilation.

KEEP OUT OF REACH OF CHILDREN

MIL-P-159 IA XIOORWEB

COMMENTS • • \leq JH PL - **1**