

ACCEPTED
NOV 2

BLP MOBILE PAINTS

Jack Tar

Marine Finishes

ACTIVE INGREDIENT	57.6%
INERT INGREDIENTS	42.4%
TOTAL	100.0%

CONTAINS 1.0% OF ANTI-FOULING AGENTS

VINYL ANTI-FOULING

473-65 BROWN

KEEP OUT OF REACH OF CHILDREN

WARNING

Causes Eye Irritation. Harmful if Absorbed Through Skin. May Be Fatal if Swallowed or Inhaled.

SEE BACK PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS

MOBILE PAINT MFG. CO., INC. THEODORE, ALABAMA

PRECAUTIONARY STATEMENTS

CONTAINS XYLENE AND METHYL
ISOBUTYL KETONE.

PHYSICAL AND CHEMICAL HAZARD.

✓ Flammable. Keep away from heat and open flame.

HAZARD TO HUMANS AND DOMESTIC ANIMALS.

✓ WARNING! May be fatal if inhaled or swallowed. Do not breathe vapor or spray mist. Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and cap or hood. While spraying and/or sanding boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

STATEMENT OF PRACTICAL TREATMENT

✓ In case of contact with the eyes, flush with plenty of water and get medical attention. In case of contact with the skin, wash with soap and water. Get medical attention if irritation persists. If product is inhaled, remove victim to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Get medical attention. If product is swallowed, drink promptly a large quantity of milk, egg whites, gelatin solution, or, if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention.

ENVIRONMENTAL HAZARDS

✓ This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of waste. Do not allow chips and dust generated during paint removal to enter water. Dispose of debris in an approved landfill.

DIRECTIONS FOR USE

✓ It is a violation of federal law to use this product in a manner inconsistent with its labeling.

This paint provides extremely good protection against fouling by barnacles, tube worms, hydroids, bryozoans, and other salt water invertebrates. The high level of cuprous oxide toxicant also inhibits the build-up of algae. Vinyl Anti-Fouling 473-65 contains a vinyl copolymer resin for a tough, lasting film and fast drying.

Vinyl Anti-Fouling 65 may be applied by roller, brush, or spray. Best results are obtained by spraying. It is very important to mix the paint thoroughly before each use to disperse any of the heavy copper pigment which may have settled. A mechanical shaker or stirrer is recommended. Use Vinyl Thinner 475-31 for clean-up and when necessary for thinning. One gallon covers approximately 150-200 square feet when applied in two coats. Do not apply this product to aluminum boats.

Allow a minimum of 4 hours dry time between coats and at least 4 hours after final coat before launching. Overnight drying is best. Conditions of high humidity or low temperature increase the minimum dry time to 8 hours.

REPAINTING INSTRUCTIONS

Clean and coat a small test area to check for lifting of the old paint. If lifting occurs, all old paint should be removed and the surface prepared and painted as shown under New Work. If no lifting occurs and adhesion is good, clean the surface by scrubbing it free of all foreign matter. When dry, properly prepare and spot prime with the appropriate primer listed under New Work. Finish by applying two 2.0 mil coats of Vinyl Anti-Fouling 473-65.

INSTRUCTIONS FOR NEW WORK

STEEL: Sandblast to white metal and apply one coat of BLP Wash Primer 9-42 according to package directions. Follow with four 1.5 mil coats of BLP Vinyl Red Lead 9-71. Allow 4 hours dry time and finish by applying two 2.0 mil coats of Vinyl Anti-Fouling 473-65.
WOOD: Apply two 2.0 mil coats of Special Vinyl Primer 5-DR-5 allowing 4 hours dry time between coats. Follow with two 2.0 mil coats of Vinyl Anti-Fouling 473-65.

FIBERGLASS: Wet sand old or new fiberglass thoroughly with a mixture of half BLP Al-Co-Sol 75-41 and half water and medium fine grit sandpaper to remove all traces of wax, mold release, or other contamination. Then apply two 2.0 mil coats of Vinyl Anti-Fouling 473-65.

STORAGE AND DISPOSAL

PROHIBITIONS

Do not contaminate water, food, or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL

Pesticide, spray mixture, or clean up rinses that cannot be used according to label instructions must be disposed of according to Federal or approved state procedures under Subtitle C of the Resource Conservation and Recovery Act.

CONTAINER DISPOSAL

Triple rinse (or equivalent). Then puncture and dispose of in a sanitary landfill or by other approved state and local procedure.

GENERAL

Consult federal, state, or local disposal authorities for approved alternative procedures. EPA EST..1719-AL-1.

NET CONTENTS
ONE GALLON
(3.79 LITERS)