

# WOOD PRESERVATIVE WATER-REPELLENT (PENTACHLOROPHENOL)

ACCEPTED  
1-22-58  
1-22-58  
1-22-58  
1-22-58

## READY TO USE

## COMPOSITION A

ACTIVE INGREDIENTS	BY WT.
PENTACHLOROPHENOL*	4.75
OTHER CHLOROPHENOLS & RELATED COMPOUNDS	5.25
PETROLEUM DISTILLATE	95.00
TOTAL	100.00

\*5.0% OF TECHNICAL PENTACHLOROPHENOL  
AS DEFINED IN FED. SPEC. TT-W-470

## DIRECTIONS

Agitate Well Before Using

This Wood Preservative Compound is easily applied. It can be applied by cold soaking - brushing - spraying with no special equipment.

This product is effective against termites when poles, fences, ladders etc are dipped or brushed with the wood preservative so that all possible surfaces are treated. Heavy timbers, fence posts and poles should be free of bark, well seasoned and soaked in the product for 24 to 48 hours to be effective in preserving against rot organisms. A minimum of three minutes for dipping wood and at least 2 flowing applications by the brush or spray method to all wood that is to come in contact with the ground, must be accomplished to obtain effective results.

**FLAMMABLE LIQUID. AVOID FIRE HAZARD.  
DO NOT STORE OR USE NEAR HEAT OR  
OPEN FLAME.**

N. Y. F. D. Permit No. Y656248

**CAUTION KEEP OUT OF REACH OF CHILDREN.**

Harmful if swallowed or absorbed through the skin. Causes skin irritation. Avoid contact with skin and eyes. In case of contact flush with plenty of water. Avoid contact with food. Do not breathe vapor or spray mist. After using or handling this material, wash well with soap and water.

U.S.D.A. REG. 1-1762 W

**TRIO CHEMICAL WORKS, INC.**

BROOKLYN, NEW YORK 11216

1-22-58