

NEW  
G  
GARLAND  
COP-EX

**POISON—IF TAKEN INTERNALLY, PHYSICIAN IS TO BE CALLED IMMEDIATELY. AVOID CONTAMINATION OF FOODSTUFFS. KEEP AWAY FROM CHILDREN AND DOMESTIC ANIMALS.**

Keep away from fires or do not smoke when applying Cop-Ex. It has a naphtha base and caution should be used. Cop-Ex does not increase inflammability of the material. When the solvents are dried out, only the metal compound is left on the surface.

**For INDUSTRIAL USE ONLY**

**USDA Registration No. 1893 - 5**

**FOR GREENHOUSES**  
**Metallic Wood Preservative-Green**  
**Active Ingredients...**

**Copper Naphthenate .... 20.5%**  
**Petroleum Solvent ..... 79.0%**

**Inert Ingredients ♦ ..... 0.5%**

**♦ Inert Ingredients Contain Traces of Free Naphthenic Acid and Water.**

**CAUTION - KEEP OUT OF REACH OF CHILDREN**

**SEE OTHER PRECAUTIONS ON THE SIDE PANEL**

*Garland Products, through Modern Coating Chemicals*

**THE GARLAND COMPANY**

**Cleveland, Ohio 44105**

**ACCEPTED**  
APR 14 1969  
UNDER THE FEDERAL INSECTICIDE ACT  
REGISTERED AND LISTED AS A PESTICIDE  
FOR ECONOMIC PEST CONTROL  
EPA REG. NO. 1893-5

**DIRECTIONS**

COP-EX FOR GREENHOUSES is recommended for unpainted surfaces only. It is recommended for new wood only.

All wood coming in direct contact with the soil should receive at least two flowing coats either by brushing or spraying. When dipping wood in COP-EX FOR GREENHOUSES, a minimum of a three minute dip is recommended.

COP-EX FOR GREENHOUSES can be reduced 1 part with 1 part COP-EX REDUCER. It can be brushed on with an ordinary paint brush. It can be sprayed or it can be dipped.

It is recommended that wood benches, flats, gerania or camellia tubs be allowed to dry three or four days after COP-EX FOR GREENHOUSES has been applied before placing soil on the surface of the treated container. The surface on which COP-EX FOR GREENHOUSES has been applied may be repainted. If repainting is desired, mix one quart of linseed oil per gallon of COP-EX FOR GREENHOUSES and apply as a priming coat. Then follow with two coats of the desired type of paint. The first coat of oil paint may show a slight staining, and for that reason, the second coat is desirable.