



LUMBER LAST

- WATER REPELLENT
- KILLS TERMITES
- STOPS ROT & STAIN

ACTIVE INGREDIENTS:

CHLORDANE TECHNICAL**	1 %
PENTACHLOROPHENOL*	4.2
other chlorophenols and related compounds	0.6
Petroleum Distillates	84
INERT INGREDIENTS:	10.2

TOTAL.....100 %

* As determined by Federal Specifications TT-W-570

**Octachloro-4,7-methanotetrahydroindane .6% and related compounds .4%
Lumber Last complies with Federal Specifications TT-W-572

CAUTION

KEEP OUT OF REACH OF CHILDREN

Harmful or Fatal If Swallowed — See Additional Warnings on Back Panel

MANUFACTURING COMPANY
PITTSBURGH, PENNSYLVANIA 15218

CONTENTS: QUART

LUMBER LAST

"Good for Wood"

Good for Builders

- KILLS TERMITES, POWDER POLY TERMITES, FUNGI when applied and for many years afterwards.
- INCREASES life of lumber 2 to 4 times
- EASIER to handle
- ODOR is mild
- PENETRATES deeply

Good for Painters

- CLEAR as varnish
- WILL NOT BLOOM
- PAINTABLE
- CUTS wasteful paint absorption
- PREVENTS paint failures
- DRIES in 24 hours with good weather

DIRECTIONS:

LUMBER LAST can be applied in several ways. In order of effectiveness they are: COLD SOAK or DIP, BRUSH, SPRAY. Degree of effectiveness is entirely dependent on amount absorbed.

COLD SOAK or DIP: Ordinary Millwork should be dipped 3 to 5 minutes for each inch of thickness. From 10 to 15 gallons of LUMBER LAST can be absorbed into 1000 board feet of lumber in this manner. Flooring could be dipped in an improvised eavetrough 'vat'. Joist ends could be soaked in an open 5 gallon paint. Heavier Construction Timbers and Posts should soak from one to 48 hours depending on thickness and whether use is to be in or above ground. Open-end 55 gallon drums are useful for this purpose. Posts to be treated should be peeled and seasoned.

BRUSHING: Apply two heavy coats, if possible, waiting 6 to 24 hours between coats, 1000 board feet of lumber will take about 5 gallons this way. Cut-ends should be brushed liberally, since these open grain ends are most receptive to moisture and rot.

SPRAYING: Use garden type sprayer. Hold nozzle 3 inches from surface. (Under 3" spray bounces, over 3" spray is lost in mist). Repeat after several hours.

IMPORTANT: Lumber to be treated must be reasonably dry for best results.

BEFORE PAINTING, treated lumber must be dry; otherwise finish will take longer to dry. Drying time depends on amount of absorption in wood and also on climatic conditions. Minimum drying time is 24 hours. LUMBER LAST IS COMPATIBLE with primers, house paints, enamels, varnishes, lacquers, oil stains. (Water stains will not take).

SHINGLE TREATMENT: LUMBER LAST makes an excellent shingle stain base; just add color ground in oil.

TERMITE CONTROL: Treatment of wood is just one step in the procedure for controlling termites. Treatment of the soil next to foundations is an extremely important step. Considerable savings can be effected with the use of ELCO CHLOR-DIEL for this purpose. Detailed and easy to follow directions are included with ELCO CHLOR-DIEL which can be supplied by your LUMBER LAST DEALER.

WARNING!

Harmful if swallowed or absorbed through skin. Causes skin irritation. Do not breathe vapor, fumes or spray mist. Do not get into eyes, on skin or on clothing. Wash thoroughly with warm water and soap. Inflammable. Avoid open flame. Don't smoke while using. Avoid contamination of food and feedstuffs. Keep away from children. Care should be taken in application to avoid grass and shrubbery.

This product is toxic to fish and wildlife. Keep out of lakes, streams and ponds. Do not contaminate water supplies by cleaning of equipment or disposal of waste and containers.

ANTIDOTE: In case of swallowing administer an antidote such as milk, raw egg white, gruel or corn starch paste. Follow with an emetic such as a tablespoonful of mustard in a glass of warm water. Call physician.

CODE #1101

USDA Reg. #1941-20

FOR ECONOMIC CONTROL UNDER NO. 1011

RECORDED
222, 1971
1941-20