

Feb. 17, 1911

2147-5

STEELAST ANTIFOULING COATING

For use on bottom of ship or boat hulls for preventing fouling

1. Exceeds Federal Specifications MIL-P-15931A.

11116466616000000000000

2. Dries tack free in 15 minutes — Hard in 45 minutes.

3. Application by spray is preferred. If necessary to brush, thin with Steelcote Thinner SSR-6 and flow on

- Do not brush out - Material handles like lacquer.

4. Application over Epo-Lux No. 100 undercoats is recommended --- not over bare surfaces.

FLAMMABLE

5. Hold coverage to 200 square feet per gallon. Apply 2 coats, allowing 3 hours or more between coats. Apply final coat, and launch boat 3 hours later for best results.

6. If necessary to thin, use only Steelast Thinner SSR-6.

CAUTION: May lift some oil and varnish type paints. Do not use without spot testing for lifting. Do not use this product over Epo-Lux No. 100 E-14M Zinc Rich Zinc Dust Primer without an intermediate coat of Epo-Lux No. 100 E-20M or E-13M.

HARMFUL OR FATAL IF SWALLOWED HARMFUL IF EATEN

Keep away from heat, sparks and open flame. Cl se container after each use. Do not apply on window sills, toys, furniture, or interior surfaces of rooms which may be used by children. Use Adequate Ventilation. Avoid contact with skin. Avoid breathing of vapor or spray mist. Wash thoroughly after handling and before eating or smoking.

U.S.D.A. Registration No. 2147.8

Printed in U.S.A, 1.71 SC

DO NOT INDUCE VOMITING

STEELCOTE MANUFACTURING CO., ST. LOUIS 3, MO., U.S.A.

ATTITUTE CONTRACTOR A SAUDICE STORIGE CONTRACTOR