CONTROLS WARPING AND SWELLING


PENTA-5 has been specially compounded with water repellent ingredients so that under ordinary conditions of exposure wood treated with FENTA-5 will not pick up noticeable amounts of moisture. This ability to repel moisture reduces the possibility of warping, swelling or shrinking and provides wood with dimensional stability. Windows and doors operate easily. After drying, paint, varnish or stain may be applied to treated wood.

WARNING

CONTAINS PETROLEUM DISTIL-LATE. IF SWALLOWED. DO NOT INDUCE VOMITING. CALL PHYSICIAN.

Do not breathe vapor or spray mist. Do not get in eyes, on skin, or on clothing. Wash thoroughly after using. Wear protective clothing and rubber gloves when handling freshly treated lumber.


DO NOT USE, POUR, SPILL, OR STORE NEAR HEAT OR OPEN FLAME




WARNING: HARMFUL OR FATAL IF SWALLOWED. KEEP OUT OF PEACH OF CHILDREN.

RIVE	ITAVE	3
COMM	and a second	Server
	<u>e posts, siding,</u> g, swelling and od.	
4.40'' .C0''' 76.00 5 00,7 14 00'' 14 cder.		U
d d	Vality - (Crave, INNOXNERONNI INNOXNERONNI INNOXNERO	

○ 利利 (A) ● (A






RMFUL OR FATAL IF SWALLOWED. **EP** OUT OF REACH OF CHILDREN.

RE ON LABEL

EPA REG NO 2413.9



PENTA-5 is ready-to-use as received. For best results wood should be completely immersed in PENTA-5. Allow 5 minutes mmersion per inch of thickness. The more PENTA-5 absorbed by the wood — the better the protection obtained. Particular care should be given to the treatment of joints and exposed end grain since this is where decay and rot usually start. For existing wood construction where dipping is impractical apply PENTA-5 liberally by brush or spray. All rotted or unsound wood should be cut out prior to treatment. Wood in contact with the ground should receive two heavy brush coats.

New posts should be peeled and seasoned before attempting treatment with PENTA-5. Following seasoning they should be coldsoaked in a large oil drum or ash can for 48 to 72 hours for each end.

Allow at least one hour between applications of PENTA-5. Treated wood should be allowed to dry at least 24 hours before application of paint or varnish. Treated wood will dry for handling in two to four hours.

Coverage: One gallon will cover 140 to 175 sq. feet by brush or spray. Use 5 to 10 gallons per thousand board feet in soaking.