

COPPER-CURE

Brand of Copper Naphthenate

★ CHECKS ROT ★ REPELS MOISTURE ★ PRESERVES LUMBER ★ SEALS WOOD

PRESERVATIVE AND WATER REPELLANT

- DIRECTIONS -

Rope and Fish lines - Brush, spray or dip until thoroughly wet. Several applications will insure added protection. COPPER-CURE is UNEXCELLED in treatment of Rope, Fish line and Boats. - Lumber and Boats - Dip Lumber three (3) minutes per inch of thickness or apply two (2) liberal coats by brush or spray. Lumber treated with COPPER-CURE will have less tendency to warp, check or swell. COPPER-CURE may be painted over upon reasonable drying allowance.

**CAUTION - KEEP OUT OF REACH OF CHILDREN
HARMFUL IF SWALLOWED**

ACTIVE INGREDIENTS

Copper Naphthenate
Petroleum Solvent

By Wt

10

90

Copper as Metal

APPERSON CHEMICALS, INC.

2903 STRICKLAND STREET

JACKSONVILLE, FLORIDA

102CC

U.S.A. REGISTRATION NO.

ACCEPTED

JUN 6 1968

UNDER THE SUPERVISION OF
UNITED STATES GOVERNMENT
FEDERAL BUREAU OF INVESTIGATION
UNDER # 2434-5

Shast

NOTE: INK AND PAPER SAMPLES MUST BE
PAPER SAMPLE INK AND PAPER WILL BE
PER SPECIFICATIONS

Turknett & Turnbull Inc

119 S. 8TH STREET PHONE 356 3991

JACKSONVILLE FLORIDA 32206