

ESTABLISHED 1870

# REGATTA YACHT PAINT

ACTIVE INGREDIENT  
Cuprous Oxide 32.0%  
(Copper as metal 44.0%)  
INERT INGREDIENTS 48.0%  
100.0%

VINYLTEx 55  
ANTI-FOULING FAST RED  
With SILICONE

**CAUTION:** KEEP OUT OF  
REACH OF CHILDREN. SEE BACK  
PANEL FOR OTHER CAUTIONS.

1 U.S. GALLON  
3.785 LITERS

MANUFACTURED BY  
**BALTIMORE COPPER PAINT CO.**

OLIVER REEDER & SON, INC.  
PROPRIETORS

BALTIMORE, MD.

NEW YORK, N. Y.

ACCEPTED

Apr. 18, 1968  
UNIVERSITY OF CALIFORNIA  
FARMACOLOGICAL RESEARCH  
FOR LOCAL USE  
ED UNDER NO. 2568-11  
BY ATTACHED DOCUMENT

VINYLTEx 55 ANTI-FOULING  
FAST RED  
With Silicone

PIGMENT		58.4%
Cuprous Oxide	39.0%	
Iron Oxide C.P.	8.4%	
Silicates	2.0%	
	100.0%	

VEHICLE		41.6%
		100.0%

Vinyl Resin	6.2%
Resin	12.8%
Silicone Vinyl Resin	6.3%
Plasticizer	4.8%
Ketones	42.0%
Aromatic Solvents	28.2%
	100.0%

USDA REG. NO. 2568-11

VINYL

Outstanding Anti-Fouling  
wood or metal.

WOODEN HULLS.  
Regatta Vinyltex 55  
evaporation with Regatta  
Anti-Fouling paint  
least 3 coats. Flow  
undercoats.

STEEL and ALUMINUM  
and two coats Regatta  
of Regatta Vinyltex

SPRAYING. Thin 10  
with Regatta Vinyltex

CAUTION-COMBUSTIBLE  
absorbed through skin.  
on clothing. In case of  
water; for eyes, immediate  
contaminated clothing be  
of this paint may cause

870

# REGATTA PAINT

55  
FAST RED  
ONE

ACTIVE INGREDIENT  
Cuprous Oxide 32.0%  
(Copper as metallic 44.0%)  
INERT INGREDIENTS 68.0%  
100.0%

ACCEPTED

Apr. 18, 1968

UNIVERSITY OF CALIFORNIA  
FISH AND GAME COMMISSION  
FOOT LOCKER 25  
EDUCATION  
11. ATTACHED

## VINYLTEX 55 ANTI-FOULING FAST RED With Silicone

PIGMENT		58.4%
Cuprous Oxide	32.0%	
Iron Oxide C.P.	8.4%	
Silicates	2.0%	
	100.0%	

VEHICLE		41.6%
		100.0%

Vinyl Resin	6.2%
Resin	12.5%
Silicone Vinyl Resin	6.3%
Plasticizer	4.8%
Ketones	42.0%
Aromatic Solvents	28.2%
	100.0%

USDA REG. NO. 2568-11

## VINYLTEX 55 ANTI-FOULING FAST RED

Outstanding Anti-Fouling Protection . . . the ultimate in a fast, hard, racing surface for wood or metal.

### DIRECTIONS

**WOODEN HULLS.** Apply directly to dry bare wood, thinning the first coat 10% with Regatta Vinyltex 54 Solvent. Apply other coats full body, replacing solvent lost by evaporation with Regatta Vinyltex 54 Solvent. Brush or spray a full wet coat so the Anti-Fouling paint will flow together eliminating any pin-holes or "holidays." Use at least 3 coats. Flow on with minimum brushing to prevent dissolving and working up intercoats.

**STEEL and ALUMINUM HULLS.** Prepare surface with Regatta Vinyltex 50 Wash Primer and two coats Regatta Vinyltex 53 Zinc Chromate Anti-Corrosive. Apply at least 2 coats of Regatta Vinyltex 55 Anti-Fouling Fast Red.

**SPRAYING.** Thin 10% with Regatta Vinyltex 54 Solvent for spraying. Wash equipment with Regatta Vinyltex 54 Solvent.

**CAUTION-COMBUSTIBLE** Keep away from heat, sparks, and open flame. Harmful if swallowed. May be absorbed through skin. Causes skin irritation. Avoid breathing spray mist. Do not get in eyes, on skin or on clothing. In case of skin contact, remove contaminated clothing and immediately wash skin with soap and water; for eyes, immediately flush with plenty of water. If irritation persists, get medical attention. Wash contaminated clothing before reuse. Avoid storage near food and feed products. Because the ingredients of this paint may cause allergic reactions to some sensitive skin, avoid prolonged contact with wet or dry paint.

OF  
BACK  
IONS.

N

BY  
ER PAINT CO.  
SON, INC.

NEW YORK, N. Y.