

ESTABLISHED 1870

REGATTA YACHT PAINT

3003

RICH RED ANTI-FOULING

**WARNING! KEEP OUT OF
REACH OF CHILDREN. SEE BACK
PANEL FOR OTHER CAUTIONS.**

1 U. S. GALLON

RICH RED ANALYSIS

PIGMENT	31.5%
Copper Resinate	10.2%
Cuprous Oxide	65.0%
Red Iron Oxide	21.5%
Mercuric Oxide	3.3%
	100.0%

VEHICLE	61.5%
Maleic-terpene Modified vinyl copolymer ..	9.8%
Denatured Alcohol ..	82.3%
Pine Oil	7.9%
	100.0%

ACTIVE INGREDIENTS	35.6%
Cupric Resinate	3.8%
(Copper as metallic 0.4%)	
Cuprous Oxide	23.8%
(Copper as metallic 20.5%)	
Mercuric Oxide	1.0%
(Mercury as metallic 0.7%)	
Pine Oil	5.0%
	33.6%

INERT INGREDIENTS64.4%
U.S.D.A. REG. NO. 2568-14

RICH RED DIRECTIONS

Stir thoroughly before and during application, and allow 1-2 hours drying time between coats and 4 hours before launching. It is not advisable to delay launching longer than 24 hours. For wooden hulls apply to bare wood or to a surface properly prepared by sanding, wire brushing, and cleaning. For best results two coats should be applied, and on new work no less than three coats. No other primer should be used. For application to metal hulls, apply first several coats of underwater primer. No thinner is normally needed . . . denatured alcohol may be used to wash brushes or replace solvent lost by evaporation.

WARNING! FLAMMABLE! Keep away from heat, sparks and open flame. CONTAINS MERCURIC OXIDE OR OTHER COMPOUNDS THAT MAY BE FATAL IF SWALLOWED. Do not apply on any interior surfaces of a dwelling, or a place used for the care of children, or on window sills, toys, cribs, and other furniture which might be chewed by children. Do not breathe vapor or spray mist. Do not get in eyes, on skin or on clothing. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use. KEEP OUT OF REACH OF CHILDREN. Use with adequate ventilation. Do not take internally. (B)

MANUFACTURED BY

BALTIMORE COPPER PAINT CO.

OLIVER REEDER & SON, INC.
PROPRIETORS

BALTIMORE, MD. 21230

NEW YORK, N.Y. 10038

Aug 10 1972

10038