ESTABLISHED 1870

REGATTA YACHT PAINT

3018

FAF BLUE

Fiberglass Anti-Fouling

CAUTION: KEEP OUT OF REACH OF CHILDREN. SEE BACK PANEL FOR OTHER CAUTIONS/

> 1 U.S. GALLON 3.785 LITERS

MANUFACTURED BY

BALTIMORE, MD. 21230

.. 1.4%

....52.2%

100.0%

ACTIVE INGREDIENT

INERT INGL DIENTS

(Copper, as metal 42.47) Bis (Tributyltin) Oxide

Cuprous Oxide ..

NEW YORK, N.Y. 10038

FAF has been formu glass. However, it w primed metal or over condition.

ACCEPTELI Stir thoroughly both wood—allowing 4 to It is not advisable to or spray gun. Ording than 10% REGATTA

UNDER THE FEDERAL INSECTICIDE FUNCICIDE AND RODENTICIDE ACT Fibreglass. Sand the FOR ECONOMIC POISON REGISTER ED UNDER NO. 2518. 45

down carefully with Solvent Wash and ci gel-coat.

An alternate method Wash and 3351 Fib necessity of sanding

Wood. Apply three Metal. Apply one of REGATTA 3630/363

Previously Coated S 3802 Xylol Solvent.

CAUTION! COMBUS' FLAME. CONTAINS any interior surfaces sills, toys, cribs and vapor or spray mist. or on clothing. In o with soap and water


Keep container close container. Destroy it

ANALYSIS

PIGMENT-64.4% Cuprous Oxide 46.4% Titanium Dioxide, Inert Extenders ... VEHICLE—35.6% Processed Rosin Total 100.0%

E.P.A. Reg. No. 2568-45

PAINT



ANALYSIS

PIGMENT-64.4%	
Cuprous Oxide Titanium Dioxide, Type III Phthalocyanine Blue	5.69
VEHICLE-35.6%	
Processed Rosin Coumarone—Indene Resin Bis (tributyltin) Oxide Aromatic Hydrocarbons Mineral Spirits	4.79 1.49 7.09
Total	100.09

E.P.A. Rog. No. 2568-45

FAF has been formulated using modern resins, selected for maximum adhesion to fibreglass. However, it will give completely satisfactory results when used on wood, properly primed metal or over most types of a previous season's anti-fouling paint that is in good condition.

ACCEPTED

UNDER THE FEDERAL INSECTICIDE ED UNDER NO. 2568. 45

DIRECTIONS

Stir thoroughly both before and during application. Apply at least two coats—three on bare wood—allowing 4 to 6 hours drying time between coats and between final coat and launch. It is not advisable to delay launch more than 3 days after final coat. Apply by brush, roller, or spray gun. Ordinarily thinning is not necessary, but where it is desired, add not more than 10% REGATTA #3800 Thinner.

SURFACE PREPARATION

FUNCICIDE AND RODENTICIDE ACT Fibreglass. Sand the bottom thoroughly, using medium grit (about #100) paper. Wipe FOR ECONOMIC POISON REGISTER down carefully with REGATTA 3830 Fibreglass Solvent Wash. Use generous quantities of Solvent Wash and clean rags in order to remove the wax-like substance from the fibreglass gei-coat.

> An alternate method of surface preparation is to use REGATTA 3840 Fibreglass Pre-Prime Wash and 3351 Fibreglass No-Sand Primer according to directions, thereby avoiding the necessity of sanding.

Wood. Apply three coats of FAF directly to bare wood.

Metal. Apply one coat of REGATTA Vinyltex 50/51 Wash Primer followed by two coats of REGATTA 3630/3631 Epoxydur Black Mastic.

Previously Coated Surfaces. Sand thoroughly, then wipe down with #3800 Thinner or 3802 Xylo! Solvent.

CAUTION! COMBUSTIBLE! DO NOT USE, POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME. CONTAINS COMPOUNDS HARMFUL OR FATAL IF SWALLOWED. Do not apply on any interior surfaces of a dwelling, or a place used for the care of children, or on window sills, toys, cribs and other furniture which might be chewed by children. Avoid breathing vapor or spray mist. Wash thoroughly after handling and before eating or smoking. KEEP OUT OF REACH OF CHILDREN. May be absorbed through skin. Do not get in eyes, on skin or on clothing. In case of contact, immediately remove contaminated clothing and wash with soap and water. Wash contaminated clothing before reuse. Causes skin irritation.

Keep container closed when not in use. Use with adequate ventilation. Do not reuse empty container. Destroy it by perforating or crushing. Burn or discard in a safe place.

ED BY

PER PAINT CO.

NEW YORK, N.Y. 10038