

7568-60

REGATTA is an anti-fouling paint based on Chlorinated Rubber. It may be used on wood, fiberglass, properly primed metal or most types of previous seasons anti-fouling paint that is in good condition.

DIRECTIONS

Stir thoroughly, both before and during application. Apply at least two coats—allowing 4 to 6 hours drying time between first coat and launch. It is not advisable to delay launch more than 3 days after final coat. Apply by brush, roller, or spray gun. Ordinarily thinning is not necessary, but where it is desired, add not more than 10% Regatta 3802 Xylol Solvent.

SURFACE PREPARATION

FIBREGLASS: Sand the bottom thoroughly, using medium grit (about #100) paper. Wipe down carefully with REGATTA 3830 Fibreglass Solvent Wash. Use generous quantities of Solvent Wash and clean rags in order to remove the wax-like substance from the fibreglass surface.

An alternate method of surface preparation is to use REGATTA 3840 Fibreglass Pre-Prime Wash and 3851 Fibreglass No Sand Primer according to directions, thereby avoiding the necessity of sanding.

WOOD: Apply three coats of REGATTA 3801 Wood Primer. Allow 4-6 hours between coats.


METAL: Apply one coat of REGATTA 3801 Metal Primer followed by two coats of REGATTA 3830 3831 Envyour Metal Wash.

PREVIOUSLY COATED SURFACES: Sand thoroughly, then wipe down with 3802 Xylol Solvent.

CAUTION! COMBUSTIBLE! DO NOT USE, POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME. CONTAINS COMPOUNDS HARMFUL OR FATAL IF SWALLOWED. Do not apply on any interior surfaces of a dwelling or a place used for the care of children, or on window sills, toys, cribs and other furniture which might be chewed by children. Avoid breathing vapors or spray mist. Wash thoroughly after handling and before eating or smoking. **KEEP OUT OF REACH OF CHILDREN.** May be absorbed through skin. Do not get in eyes, on face or on clothing. In case of contact, immediately remove contaminated clothing and wash with soap and water. Wash contact area with plenty of water before reuse. Causes skin irritation.

Keep container closed when not in use. Use with adequate ventilation. Do not reuse empty container. Destroy it by perforating or crushing. Burn or discard in a safe place. Do not contaminate water by cleaning equipment or disposal of waste.

BEST DOCUMENT AVAILABLE



ESTABLISHED 1870

ACTIVE INGREDIENTS

Cuprous Oxide (Copper as metal 29.35%) 32.42%
Tributyltin Fluoride 1.85%

INERT INGREDIENTS

65.73%

100.00%

ANALYSIS

PIGMENT 51.87%
Copper Phthalocyanine Blue (IX-A) 1.21%
Titanium Dioxide (Type II) 6.60%
Chrome Yellow 3.78%
Zinc Oxide 3.79%
Tributyltin Fluoride 1.85%
Cuprous Oxide 32.42%
Inert Pigment 2.22%
VEHICLE 48.13%
Chlorinated Rubber 7.81%
Rosin 5.69%
Tricresyl Phosphate 2.58%
Aromatic Hydrocarbons 30.49%
Additives 1.56%
100.00%

1 U.S. GALLON
3.785 LITERS

302 - Baltotox Red
Anti-Fouling

ESTABLISHED 1870

ACTIVE INGREDIENTS

Cuprous Oxide (Copper as metal 30.75%)
Tributyltin Fluoride

INERT INGREDIENTS

BEST DOCUMENT AVAILABLE

ANALYSIS

PIGMENT 49.56%

Cuprous Oxide
Tributyltin Fluoride
Red Iron Oxide
Zinc Oxide
Inert Pigment

VEHICLE 50.44%

Chlorinated Rubber
Rosin
Tricresyl Phosphate
Aromatic Hydrocarbons
Additives

See Back of Box for Directions
and Caution