

Regatta®

ESTABLISHED 1870

Anti-Fouling

3048 BALTOGUARD BLUE WITH TBTF



PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS (and Domestic Animals)

DANGER

Corrosive. Causes severe eye damage and skin irritation. Do not get in eyes, on skin or on clothing. Wear goggles or face shield and rubber gloves when handling. May be fatal if swallowed. Do not breathe vapor or spray mist. Use with adequate ventilation. Wash thoroughly with soap and water after handling and before eating and smoking.

FIRST AID

In case of contact immediately flush eyes or skin with plenty of water for at least 15 minutes. For eyes call a physician. Remove and wash contaminated clothing before reuse. If swallowed drink 1 or 2 glasses of water and induce vomiting by touching back of throat with finger or blunt object. Do not induce vomiting or give anything by mouth to an unconscious person. Get medical attention. If inhaled remove to fresh air. If not breathing give artificial respiration.

ENVIRONMENTAL HAZARDS

Do not contaminate water by cleaning of equipment or disposal of wastes.

PHYSICAL OR CHEMICAL HAZARDS

Do not use or store near heat or open fire.

Note—When product is used in confined areas or applied by spraying wear protective clothing and a pesticide respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U. S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

ACTIVE INGREDIENTS

Tributyltin Fluoride	12.94%
INERT INGREDIENTS	87.06%
	100.00%

KEEP OUT OF THE REACH OF CHILDREN

DANGER

SEE SIDE PANEL FOR ADDITIONAL
PRECAUTIONARY STATEMENTS

EPA Establishment No. 2588-MD-01
EPA Registration No. 2588-69

JOTUN BCP MARINE COATINGS

ANALYSIS

PIGMENT 23.30%	
Copper Phthalocyanine Blue (IX-A)	1.79%
Titanium Dioxide (Type II)	3.35%
Zinc Oxide	8.45%
Tributyltin Fluoride	12.94%
Inert Pigment	1.77%
VEHICLE 74.70%	
Chlorinated Rubber	12.12%
Rosin	8.83%
Tricresyl Phosphate	4.00%
Aromatic Hydrocarbons	47.33%
Additives	2.42%
	100.00%

(B-259)

ACCEPTED

OCT 12 1979

Under the Federal Insecticide, Fungicide, and Rodenticide Act, as amended, for the pesticide registered under EPA Reg. No. 2568-69

54

Baltog
fibregl
is in

Stir th
4 to 6
more
is not

FIBRE
down
Solven
gel-co

An aft
Wash
necess

WOOD

METAL
REGAT

PREVH
Solven

Regatta

ESTABLISHED 1870®

Anti-Fouling

UE



ANALYSIS

PIGMENT 23.30%	
Copper Phthalocyanine Blue (IX-A)	1.79%
Titanium Dioxide (Type II)	3.35%
Zinc Oxide	5.45%
Tributyltin Fluoride	12.94%
Inert Pigment	1.77%
VEHICLE 74.70%	
Chlorinated Rubber	12.12%
Resin	8.83%
Trierythyl Phosphate	4.00%
Aromatic Hydrocarbons	47.33%
Additives	2.42%
100.00%	

(B-259)

ACCEPTED

OCT 12 1979

Under the Federal Insecticide, Fungicide, and Rodenticide Act, as amended, for the pesticide registered under EPA Reg. No. 2568-69

DIRECTIONS

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

Baltoguard is an anti-fouling paint based on Chlorinated Rubber. It may be used on wood, fiberglass, properly primed metal or most types of previous seasons anti-fouling paint that is in good condition.

Stir thoroughly both before and during application. Apply at least two coats—allowing 4 to 6 hours drying time between final coat and launch. It is not advisable to delay launch more than 3 days after final coat. Apply by brush, roller, or spray gun. Ordinary thinning is not necessary, but where it is desired, add not more than 10% Regatta 3802 Xylol Solvent.

SURFACE PREPARATION

FIBREGLASS: Sand the bottom thoroughly, using medium grit (about #100) paper. Wipe down carefully with REGATTA 3840 Fibreglass Solvent Wash. Use generous quantities of Solvent Wash and clean rags in order to remove the wax-like substance from the fibreglass gel-coat.

An alternate method of surface preparation is to use REGATTA 3840 Fibreglass Pre-Prime Wash and 3351 Fibreglass No-Sand Primer according to directions, thereby avoiding the necessity of sanding.

WOOD: Apply three coats Baltoguard directly to bare wood. Allow 4-6 hours between coats.

METAL: Apply one coat of REGATTA Vinyltex 50/51 Wash Primer followed by two coats of REGATTA 3630/3631 Epoxydur Black Mastic.

PREVIOUSLY COATED SURFACES: Sand thoroughly, then wipe down with 3802 Xylol Solvent.

STORAGE & DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

Do not reuse empty containers.

Wrap container and put in trash collection.

1 U.S. Gallon

3.785 LITERS

JOTUN — BALTIMORE COPPER PAINT CO.

501 KEY HIGHWAY BALTIMORE, MD. 21230 (301) 539-0045

LDREN

MARINE COATINGS