

**'INTERLUX' ANTIFOULING PAINT
RACING BRONZE NO. 24
(READY MIXED)**

For the bottoms of racing and sailing yachts or low powered craft which require a smooth, frictionless surface and freedom from fouling over lengthy periods.

DIRECTIONS

The bottom of a yacht which has been in service for some time, or is placed high and dry over the winter, will probably have become somewhat rough. For this reason, and also to give the fresh composition fair conditions to enable it to function as intended, the old coatings should be scraped down to the wood and well rubbed to remove all traces of loose paint, etc. The surface should then be given a priming coat of 24 'INTERLUX' ANTIFOULING PAINT RACING BRONZE, which is made with properties allowing for its application directly to bare wood. No special undercoat is necessary.

All irregularities, seams and cracks may then be filled with 'INTERLUX' TROWEL CEMENT which normally dries sufficiently hard in several hours, to allow for sanding down smooth.

Next apply at least two, or preferably three coats 24 'INTERLUX' ANTIFOULING PAINT RACING BRONZE, allowing about two hours for drying between coats.

It is recommended that at least two hours be given the last coat to harden, and that the launching take place within five hours after the last coat is applied. However, when necessary, the launching may be delayed overnight as the composition is not then exposed to direct rays of sunlight.

FIBERGLASS — Wipe fiberglass thoroughly with 202 'INTERLUX' FIBERGLASS SOLVENT WASH to remove mold release agent and apply one coat 200 'INTERLUX' FIBERGLASS PRIMER. After 2-3 hours drying time apply two coats 24 ANTIFOULING PAINT RACING BRONZE.

OR

Sand fiberglass thoroughly with 80 Grit Production Paper. Wipe surface clean with 216 'INTERLUX' SPECIAL SOLVENT. Apply two coats of 24 ANTIFOULING PAINT RACING BRONZE.

Stir thoroughly before and while being used.


Use good quality brushes to insure smoothness.

Always see that the surface is dry and clean before painting.

If found a little heavy, add a small quantity of 216 'INTERLUX' SPECIAL THINNER.

APPROXIMATE COVERAGE on average surfaces is 500 sq. ft. per gallon, 2 coats.

International



Paints

ONE U.S. GALLON

WARNING!
KEEP OUT OF REACH OF CHILDREN
See other warnings on back panel

ACCEPTED

10/12/70


29324

Interlux[®]
FOR EXTERIOR OR INTERIOR USE

**Almost
Indestructible**

**24 ANTIFOULING PAINT
RACING BRONZE**


ACTIVE INGREDIENTS	PER CENT
Copper	34.0%
INERT INGREDIENTS	66.0%
	100.0%



International Paint Company, Inc.

NEW YORK, N. Y. 10006 • SAN FRANCISCO, CAL. 94108 • NEW ORLEANS, LA. 70126

International



Paints

ONE U.S. GALLON

WARNING!
KEEP OUT OF REACH OF CHILDREN
See other warnings on back panel

ACCEPTED

10/12/70

2693-24

Interlux®
FOR EXTERIOR OR INTERIOR USE

**Almost
Indestructible**

**24 ANTIFOULING PAINT
RACING BRONZE**

FACTORIES

U.S.A.	UNION, N. J.	HOLLAND	RIJSDWIJK
U.S.A.	SAN FRANCISCO	ITALY	GENOA
U.S.A.	NEW ORLEANS	ITALY	TRIESTE
AUSTRALIA	SYDNEY	MEXICO	MEXICO CITY
BRAZIL	RIO DE JANEIRO	NEW ZEALAND	AUCKLAND
CANADA	MONTREAL	NEW ZEALAND	WELLINGTON
CANADA	REGINA	NIGERIA	IKEJA
CANADA	VANCOUVER	NORWAY	BERGEN
DENMARK	COPENHAGEN	PORTUGAL	SETUBAL
ENGLAND	FELLING-ON-TYNE	SCOTLAND	GLASGOW
FRANCE	ROUEN	SPAIN	BILBAO
GERMANY	HAMBURG	SWEDEN	GOTHENBURG
		VENEZUELA	MARACAIBO

WARNING

Harmful if swallowed. Do not use or store near heat or open flame.

Use with adequate ventilation.


Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use.

U.S.D.A. Reg. No. 2693-24

International Paint Company, Inc.

NEW YORK, N. Y. 10006 • SAN FRANCISCO, CALIF. 94108 • NEW ORLEANS, LA. 70126

REGISTERED



TRADE MARK